

台塑聚丙烯塑膠 FORMOSA POLYPROPYLENE



永嘉烯 YUNGSOX

5018

無規共聚物 RANDOM COPOLYMER

用途 Applications

- 吹瓶 Blow molding
- 點滴瓶 Pharmaceutical bottle

特性 Characteristics

- 抗化學藥品性佳
Good resistance to chemical

物性 Typical Properties

項目 Properties	單位 Unit	檢驗方法 Test Method	平均值 Typical Value
熔融指數 Melt Index	g/10min	ISO1133	1.7
密度 Density	g/cm ³	ISO1183	0.90
熔點 Melting Point	°C	DSC	146
熱變形溫度 Heat Deflection Temperature	°C	ISO75	90
軟化點溫度 Vicat Softening Temperature	°C	ISO306	120
降伏點拉力強度 Tensile Strength at Yield	Kg/cm ²	ISO527	250
斷裂點伸長率 Tensile Elongation at Break	%	ISO527	500
洛氏硬度 Rockwell Hardness	R scale	ISO2039	90
剛性係數 Flexural Modulus	Kg/cm ²	ISO178	9,500
IZOD 衝擊強度 IZOD Impact Strength	Kg.cm/cm notch	ISO 180	23°C 8
			-20°C ---
收縮率 Mold Shrinkage	%	FPC Method	1.3-1.7

本表數據為代表值，僅供選擇品級用途之參考

The details given in this data sheet are our standard value but not specification guaranteed.

FDA 認可 FDA Approval

永嘉烯 5018 符合美國食品及藥物管理局 21 CFR 177.1520 之規範，可直接與食物接觸。

Yungsox 5018 resin meets the FDA requirements in the Code of Federal Regulations in 21 CFR 177.1520 for food contact.

USP 生物試驗 USP Biological Reactivity Tests

永嘉烯 5018 通過美國藥典塑膠第六級試驗。

Yungsox 5018 resin meets the requirements of USP Plastic Class VI.

Jan 2015

技術服務 Client service

電話 TEL: 886-7-6419911 ext. 313

傳真 FAX: 886-7-6425581