

POLYPROPYLENE



Polymer Composite

HI-PRENE HG41T

Typical Properties	Test Conditions	Test Method	Units	Result
Physical				
Melt Flow Rate	2.16 kg @230°C	ASTM D1238	g/10min	5
Density	-	ASTM D792	g/cm ³	1.11
Mechanical				
Tensile Strength at Yield	50 mm/min	ASTM D638	MPa	65
Elongation at Break	50 mm/min	ASTM D638	%	4
Flexural Strength	10 mm/min	ASTM D790	MPa	85
Flexural Modulus	10 mm/min	ASTM D790	MPa	3,700
Izod Impact	@23°C, Notched	ASTM D256	J/m	75
Rockwell Hardness	-	ASTM D785	R scale	110
Thermal				
Heat Deflection Temperature	1.8 MPa	ASTM D648	°C	160

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com