

POLYPROPYLENE



Polymer Composite

HI-PRENE HT44B

Typical Properties	Test Conditions	Test Method	Units	Result
Physical				
Melt Flow Rate	2.16 kg, @230°C	ASTM D1238	g/10min	14
Density	-	ASTM D792	g/cm ³	1.25
Mechanical				
Tensile Strength at Yield	50 mm/min	ASTM D638	MPa	36
Elongation at Break	50 mm/min	ASTM D638	%	6
Flexural Strength	1.27 mm/min	ASTM D790	MPa	60
Flexural Modulus	1.27 mm/min	ASTM D790	MPa	5,650
Izod Impact	@23°C, Notched	ASTM D256	J/m	32
Rockwell Hardness	-	ASTM D785	R scale	103
Thermal				
Heat Deflection Temperature	0.45 MPa	ASTM D648	°C	152

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com