

POLYPROPYLENE



Polymer Composite

HI-PRENE MG63HH

Typical Properties	Test Conditions	Test Method	Units	Result
Physical				
Melt Flow Rate	2.16 kg @230°C	ASTM D1238	g/10min	30
Density	-	ASTM D792	g/cm ³	1.11
Mechanical				
Tensile Strength at Yield	50 mm/min	ASTM D638	MPa	55
Elongation at Break	50 mm/min	ASTM D638	%	6
Flexural Strength	30 mm/min	ASTM D790	MPa	85
Flexural Modulus	30 mm/min	ASTM D790	MPa	4,100
Izod Impact	@23°C, Notched	ASTM D256	J/m	65
Izod Impact	@-10°C, Notched	ASTM D256	J/m	45
Rockwell Hardness	-	ASTM D785	R scale	103
Thermal				
Heat Deflection Temperature	0.45 MPa	ASTM D648	°C	155

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com