

POLYPROPYLENE



Polymer Composite

HI-PRENE MM71T

Typical Properties	Test Conditions	Test Method	Units	Result
Physical				
Melt Flow Rate	2.16 kg @230°C	ISO 1133	g/10min	35
Density	-	ISO 1183	g/cm ³	0.98
Mechanical				
Tensile Strength at Yield	50 mm/min	ISO 527	MPa	23
Elongation at Break	50 mm/min	ISO 527	%	80
Flexural Strength	30 mm/min	ISO 178	MPa	36
Flexural Modulus	30 mm/min	ISO 178	MPa	2,530
Izod Impact	@23°C, Notched	ISO 180	kJ/m ²	33
Izod Impact	@-10°C, Notched	ISO 180	kJ/m ²	10
Rockwell Hardness	-	ISO 2039	R scale	72
Thermal				
Heat Deflection Temperature	0.45 MPa	ISO 75	°C	113

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com