

POLYPROPYLENE



Polymer Composite

HI-PRENE MT63I

Typical Properties	Test Conditions	Test Method	Units	Result
Physical				
Melt Flow Rate	2.16 kg @230°C	ISO 1133	g/10min	20
Density	-	ISO 1183	g/cm ³	1.04
Mechanical				
Tensile Strength at Yield	50 mm/min	ISO 527	MPa	20
Elongation at Break	50 mm/min	ISO 527	%	340
Flexural Strength	2 mm/min	ISO 178	MPa	32
Flexural Modulus	2 mm/min	ISO 178	MPa	1,850
Izod Impact	@23°C, Notched	ISO 180	kJ/m ²	38.5
Izod Impact	@-30°C, Notched	ISO 180	kJ/m ²	5.1
Thermal				
Heat Deflection Temperature	0.45 MPa	ISO 75	°C	108

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com