

## POLYPROPYLENE



## Polymer Composite

## HI-PRENE RM60B7030

| Typical Properties          | Test Conditions | Test Method | Units             | Result |
|-----------------------------|-----------------|-------------|-------------------|--------|
| Physical                    |                 |             |                   |        |
| Melt Flow Rate              | 2.16 kg @230°C  | ASTM D1238  | g/10min           | 21     |
| Density                     | -               | ASTM D792   | g/cm <sup>3</sup> | 0.92   |
| Mechanical                  |                 |             |                   |        |
| Tensile Strength at Yield   | 50 mm/min       | ASTM D638   | MPa               | 27     |
| Elongation at Break         | 50 mm/min       | ASTM D638   | %                 | 49     |
| Flexural Strength           | 10 mm/min       | ASTM D790   | MPa               | 32     |
| Flexural Modulus            | 10 mm/min       | ASTM D790   | MPa               | 1,330  |
| Izod Impact                 | @23°C, Notched  | ASTM D256   | J/m               | 76.5   |
| Thermal                     |                 |             |                   |        |
| Heat Deflection Temperature | 0.45 MPa        | ASTM D648   | °C                | 112    |

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com