

POLYPROPYLENE



Polymer Composite

HI-PRENE RM60BLK

Typical Properties	Test Conditions	Test Method	Units	Result
Physical				
Melt Flow Rate	2.16 kg @230°C	ASTM D1238	g/10min	9.3
Density	-	ASTM D792	g/cm ³	0.93
Mechanical				
Tensile Strength at Yield	50 mm/min	ASTM D638	MPa	27
Elongation at Break	50 mm/min	ASTM D638	%	110
Flexural Strength	10 mm/min	ASTM D790	MPa	32
Flexural Modulus	10 mm/min	ASTM D790	MPa	1,360
Izod Impact	@23°C, Notched	ASTM D256	J/m	60
Thermal				
Heat Deflection Temperature	0.45 MPa	ASTM D648	°C	104

※ Results may vary depending on environmental conditions and /or devices.

May, 2020

www.gspolymer.com