

LLDPE

4141C

LLDPE for stretch wrap

Application

Film, Wrap film, General film

Characteristics

Excellent mechanical properties, Excellent optical properties (transparency, gloss), Low Fisheye

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238 (190°C, 2.16kg)	g/10min	2.4
Density	ASTM D1505	g/cm ³	0.92
Vicat softening point	ASTM D1525	°C	93

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Film properties

Item	Test Method	Unit	Typical value
Tensile strength at break (MD)	ASTM D882	kg/cm ²	380
Tensile strength at break (TD)	ASTM D882	kg/cm ²	230
Elongation at break (MD)	ASTM D882	%	510
Elongation at break (TD)	ASTM D882	%	625
Elmendorf tear strength (MD)	ASTM D1922	kg/cm ²	110
Elmendorf tear strength (TD)	ASTM D1922	kg/cm ²	200
Dart drop impact strength	ASTM D1709	g	100
Haze	ASTM D1003	%	0.9

Note: The above data is the result of measuring a 38 µm film.

Processing conditions

Item	Unit	Typical value
Hopper unit	°C	170 ~ 190
Cylinder temperature	°C	180 ~ 230
Head temperature	°C	200 ~ 250
Temperature of Die unit	°C	220 ~ 250

※ Actual temperature conditions vary depending on extruder conditions such as screw type and die structure, film standard, extrusion amount, etc.



Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16, 18-20F, Hanwha
Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,
Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.