

EVA

E181L

EVA for extrusion coating

Application

Coating, BOPP coating

Characteristics

Excellent transparency, High speed processability, Neck-in, Adhesive

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238 (190°C, 2.16g)	g/10min	25
Density	ASTM D1505	g/cm ³	0.940
VA content	HTC Method	%	18
Melt temperature	HTC Method	°C	83
Tensile strength(at break)	ASTM D638	kg/cm ²	125
Elongation (at break)	ASTM D638	%	>600
Vicat softening point	ASTM D1525	°C	56
Brittleness temperature	ASTM D746	°C	<-70

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Processing conditions

Item	Unit	Typical value
Hopper unit	°C	Room Temp.
Barrel temperature	°C	130 ~ 240
Extrusion temperature	°C	220 ~ 240
Temperature of Die unit	°C	230 ~ 240

※ Optimal extrusion molding conditions may vary depending on facility specifications such as screw type, die structure, and extrusion amount, and please use the above figures as reference.

Certification

Hanwha TotalEnergies Petrochemical are limitations in applying Hanwha TotalEnergies E181L for food packaging purposes.

For further inquiries, please contact Customer Technical Service.



Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha
Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,
Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.