

HDPE

F920A

HDPE for Film

Application

Film, General film, Shopping bag, Food packaging film

Characteristics

Excellent mechanical properties, Excellent processability, Transparency, Compatibility with LDPE and LLDPE

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238	g/10min	1.0
Density	ASTM D1505	g/cm ³	0.956

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Film properties

Item	Test Method	Unit	Typical value
Thickness	-	μm	25
Haze	ASTM D1003	%	20
Gloss (45°)	ASTM D2457	%	40
Tensile strength at yield (MD)	ASTM D882	kg/cm ²	500
Tensile strength at yield (TD)	ASTM D882	kg/cm ²	350
Tensile elongation at break (MD)	ASTM D882	%	550
Tensile elongation at break (TD)	ASTM D882	%	750
Elmendorf tear strength (MD)	ASTM D1922	kg/cm ²	20
Elmendorf tear strength (TD)	ASTM D1922	kg/cm ²	500

Note: The above physical property value is a representative value for reference and is not a product quality standard.

Processing conditions

Item	Unit	Typical value
Screw diameter	mmΦ	50
Die diameter	mmΦ	100
Blow up ratio	-	2.5
Processing temperature	°C	160 ~ 190

**Certification**

Hanwha TotalEnergies Petrochemical F920A satisfies the 21 CFR 177.1520 regulations, the food packaging standards of the U.S. Food and Drug Administration (FDA).
For further inquiries, please contact Customer Technical Service.

**Contact
information**

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha
Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,
Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.