

HDPE

Y910A

HDPE with extruded elongation

Application

Elongation, Flat Yan, Monofilament, Fishing net

Characteristics

Excellent processability, Excellent mechanical properties, Thermal resistance stability

Physical properties

Item	Test Method	Unit	Typical Value
Melt index	ASTM D1238 (190°C, 2.16kg)	g/10min	1.0
Density	ASTM D1505	g/cm ³	0.956
Tensile strength (at yield)	ASTM D638	kg/cm ²	250
Tensile strength(at break)	ASTM D638	kg/cm ²	350
Izod Impact Strength (23°C)	ASTM D256	kg cm/cm	20
Flexural modulus	ASTM D790	kg/cm ²	9000
Elongation (at break)	ASTM D638	%	>500
Vicat softening point	ASTM D1525	°C	125
Rockwell hardness	ASTM D785	R scale	50

Note) Data shown above are representative values for reference purposes only, and not to be construed as specifications.

Processing conditions

Item	Unit	Typical value
Hopper unit	-	Room Temp.
Cylinder (supply and compression unit)	°C	180 ~ 220
Cylinder (measurement unit) and die unit	°C	230 ~ 260
stretching ratio	Times	9 ~ 12
Coolant temperature	°C	30 ~ 70 (Stretching temp 100°C)

※ Actual extrusion and compression molding conditions should be appropriately selected according to facility specifications such as screw type, die design, extrusion volume, etc.

Certification

Hanwha TotalEnergies Petrochemical are limitations in applying Hanwha TotalEnergies Y910A for food packaging purposes.

For further inquiries, please contact Customer Technical Service.



Contact information

Hanwha TotalEnergies Petrochemical co. Ltd.
www.htpchem.com

Sales Office
04525 No.92, Sejong-daero, Jung-gu, 16,18-20F, Hanwha
Finance Plaza, Seoul, Republic of Korea
16th floor of Hanwha Financial Plaza

Customer Technical Service
31900 103, Dokgot 2-ro, Daesan-eup, Seosan-si,
Chungcheongnam-do, Republic of Korea
T. 041-660-6190 F. 041-660-6189

Disclaimer

This document is copyrighted by Hanwha TotalEnergies Petrochemical. All information is for reference only and is not the specifications of the final product. Customers should make their own judgments as to whether our products and information serve a particular purpose and what regulations apply to customers' use of such products. Hanwha TotalEnergies Petrochemical is not responsible or obligated for the contents of this document. Hanwha TotalEnergies Petrochemical provides no warranties of any kind, either express or implied (such as merchantability and or fitness for a particular purpose, etc.) with respect to any information contained in this material. Hanwha TotalEnergies Petrochemical may arbitrarily change the contents of this material without prior notice.