

HANWHA

Ethylene Vinylacetate Copolymer

1828

Base Resin for wire & Cable Compound

MELT INDEX 4.0

VA CONTENT 28.0

HANWHA EVA 1828 is manufactured by high pressure autoclave process and designed for base resin of variety of wire & cable compounds such as semi-conductive compound, flame retardant compound. EVA 1828 is well known for its excellent processability, filler loadability and high quality assurance.

■ Outstanding Properties

Excellent Foam Molding Property
Very Good Mechanical Properties
Excellent Loading Property of Various Fillers

■ Processing Conditions

Kneader : 70 ~ 90°C
Roll Mill : 80°C

■ Additives

Antioxidant

■ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	4.0
VA Content	wt%	HCC Method ⁽³⁾	28.0
Density	g/cm ³	ASTM D1505	0.950
Vicat Softening Point	°C	ASTM D1525	44
Melting Point	°C	ASTM D3417	75
Tensile Strength at Break	Kg/cm ²	ASTM D638	190
Elongation at Break	%	ASTM D638	800
Brittleness Temperature, F ₀	°C	ASTM D746	<-76
Hardness	Shore A	ASTM D2240	79

1. These are typical properties: not to be construed as specification.
2. The value for this property is dependent on part geometry and fabrication conditions.
3. Elemental Analyzer and FT-IR



Hanwha B/D, 1 Changgyo-dong, Chung-ku, Seoul, Korea. Tel : 82-2-729-1292 Fax : 82-2-729-3000