

HANWHA

Low Density Polyethylene

5306

Blown Film Grade

MELT INDEX **3.0**
DENSITY **0.921**

HANWHA LDPE 5306 is manufactured by DOW tubular high pressure process and designed for variety of film application such as high transparent package film. LDPE 5306 has well balanced property of high clarity, mechanical property and processability.

This product complies with U.S. FDA regulation 21 CFR 177.1520 (c) 2.1.

■ Outstanding Properties

Excellent Optical Property
 Good Mechanical Property
 Good Processability

■ Processing Conditions

Melt Temperature : 140 ~ 170°C
 Blow-up Ratio : 2 ~ 3
 Optimum Gage Range : 0.025 ~ 0.1 mm

■ Additives

Anti oxidant, Slip agent, Anti-block agent

■ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	3.0
Density	g/cc	ASTM D1505	0.921
Vicat Softening Point	°C	ASTM D1525	88
Melting Point	°C	HCC Method	110
Tensile Strength at Break	kg/cm ²	ASTM D638	110
Elongation at Break	%	ASTM D638	650
Brittleness Temperature, F ₀	°C	ASTM D746	< -76
Film Properties	Unit	Test Method	Value
Film Thickness	mm	HCC Method	0.03
Tensile Strength at Break MD	kg/cm ²	ASTM D882	230
TD			180
Elongation at Break MD	%	ASTM D882	350
TD			550
Tensile Tear Strength MD	kg/cm	ASTM D1004	90
TD			85
Dart Impact Strength	g	ASTM D1709	85
Haze	%	ASTM D1003	4.0

1. These are typical properties : not to be construed as specification.
2. The value for this property is dependent on part geometry and fabrication conditions.



Hanwha B/D, 1 Changgyo-dong, Chung-ku, Seoul, Korea. Tel : 82-2-729-2700 Fax : 82-2-729-2999