

HANWHA

M1835HN

Metallocene LLDPE

Cast Stretch wrap, Diaper Film, Cast Film
Blown Film

MELT INDEX 3.5
DENSITY 0.916

HANWHA mLLDPE M1835HN is manufactured by Unipol process and designed for cast stretch wrap and diaper film production. mLLDPE M1835HN has well balanced property of mechanical property, processability and optical property

This product complies with U.S. FDA regulation 21 CFR 177.1520 (c) 3.1.a.

■ Outstanding Properties

Mechanical Property
Low Temperature Sealing Property
Optical Property
Processability

■ Processing Conditions

Melt Temperature : 150 ~ 250 °C
Optimum Gage Range : 0.01 ~ 0.1 mm

■ Additives

Antioxidant

■ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	3.5
Density	g/cc	ASTM D1505	0.916
Vicat Softening Point	°C	ASTM D1525	99
Melting Point	°C	HCC Method	119
Tensile Strength at Break	kg/cm ²	ASTM D638	420
Elongation at Break	%	ASTM D638	770
Brittleness Temperature, F ₀	°C	ASTM D746	< -76
Film Properties	Unit	Test Method	Value
Film Thickness	mm	HCC Method	0.05
Tensile Strength at Break MD	kg/cm ²	ASTM D882	440
TD			440
Elongation at Break MD	%	ASTM D882	750
TD			790
Elmendorf Tear Strength MD	Kg/cm	ASTM D1004	780
TD			870
Dart Impact Strength	g	ASTM D1709	400
Haze	%	ASTM D1003	3

1. These are typical properties : not to be construed as specification.

2. The value for this property is dependent on part geometry and fabrication conditions.



Hanwha Solutions

Hanwha B/D, 1 Changgyo-dong, Chung-ku, Seoul, Korea. Tel : 82-2-729-2821 Fax : 82-2-729-3000