

HANWHA

M2010EA

Metallocene LLDPE

Agricultural Film, Blown Film

MELT INDEX 1.0
DENSITY 0.920

HANWHA mLLDPE M2010EA is manufactured by Unipol process and designed for general purpose and agricultural film. mLLDPE M2010EA has well balanced property of mechanical property, processability and optical property

This product complies with U.S. FDA regulation 21 CFR 177.1520 (c) 3.1.a.

■ Outstanding Properties

Mechanical Property
Optical Property
Low Temperature Sealing Property
Processability

■ Processing Conditions

Melt Temperature : 150 ~ 190 °C
Blow-up Ratio : 2 ~ 3
Optimum Gage Range : 0.03 ~ 0.1 mm

■ Additives

Antioxidant, Processing Aid, Anti Blocking agent, Slip agent

■ Physical Properties

Physical Properties	Unit	Test Method	Value
Melt Index	g/10min	ASTM D1238	1.0
Density	g/cc	ASTM D1505	0.920
Vicat Softening Point	°C	ASTM D1525	94
Melting Point	°C	HCC Method	113
Tensile Strength at Break	kg/cm ²	ASTM D638	440
Elongation at Break	%	ASTM D638	750
Brittleness Temperature, F ₀	°C	ASTM D746	< -76
Film Properties	Unit	Test Method	Value
Film Thickness	mm	HCC Method	0.05
Tensile Strength at Break MD	kg/cm ²	ASTM D882	440
TD			320
Elongation at Break MD	%	ASTM D882	400
TD			520
Elmendorf Tear Strength MD	Kg/cm	ASTM D1004	470
TD			860
Dart Impact Strength	g	ASTM D1709	490
Haze	%	ASTM D1003	9

1. These are typical properties : not to be construed as specification.

2. The value for this property is dependent on part geometry and fabrication conditions.



Hanwha B/D, 1 Changgyo-dong, Chung-ku, Seoul, Korea. Tel : 82-2-729-2821 Fax : 82-2-729-3000