



HIPTEN 15180

HIPTEN[®] 15180 is low density polyethylene resin for production of injection moulding articles and as a basis for masterbatches.

PROCESSING RECOMMENDATIONS:

Processing temperature: 180-200°C.

PROPERTIES:

PROPERTY	TEST METHOD	UNIT	VALUE
DENSITY	ISO 1183	kg/m ³	915
MELT FLOW RATE (190 °C/2,16 kg)	ISO 1133	g/10 min	18
VICAT SOFTENING POINT	ISO 306	°C	96

APPLICATION:

Production of masterbatches, injection moulding of general purpose articles.

HIPTEN[®] 15180 has Health Certificate issued by Institute for Health Protection of Serbia.

The values in this review are characteristic and are provided for guidance purposes only.

For any technical information about our products please mail to laboratorija@hip-petrohemija.co.yu