

POKETONE® M33AS1A

Description

Lubricated high-flow injection molding grade

Physical Properties	ASTM	Value	ISO	Value
Density	D792	1.24 g/cm ³	1183	1.24 g/cm ³
Shore D hardness	D2240		868	75
Hardness Rockwell	D785	113	2039	
Water absorption equilibrium at RH 50%	D570	0.6 %	62	0.6 %
Water absorption at Saturation	D570	2.2 %	62	2.2 %
Melt flow index 240°C/2.16kg	D1238	49 g/10 min	1133	46 ml/10 min
Mold Shrinkage	D955		294-4	
	MD, 3 mm	2.0 %		
	TD, 3 mm	2.0 %		
	MD, 2 mm	1.6 %		
	TD, 2 mm	1.6 %		

Mechanical Properties	ASTM	Value	ISO	Value
Tensile strength at yield	D638	60 MPa	527-1	60 MPa
Tensile modulus	D638	1,550 MPa	527-1	1,450 MPa
Tensile elongation at yield	D638	21 %	527-1	21 %
Tensile elongation at break	D638	200 %	527-1	200 %
Flexural strength	D790	57 MPa	178	56 MPa
Flexural modulus	D790	1,500 MPa	178	1,400 MPa
Unnotched Izod impact strength	D256		180/1U	
Notched Izod impact strength	D256	76 J/m	180/1A	7 kJ/m ²
Unnotched Charpy impact strength	D6110		179/1eU	
Notched Charpy impact strength	D6110		179/1eA	7 kJ/m ²
Falling dart impact strength			6603-2	

Thermal Properties	ASTM	Value	ISO	Value
Melting temperature	D3418	222 °C	11357	222 °C
Coefficient of linear thermal expansion, 25 ~ 55°C	E831			
	TD	9.7×10 ⁻⁵	11359	
	MD	1.0×10 ⁻⁴		
Vicat softening point	D1525		306/B50	
	5 kg	187 °C	50 N	187 °C
Heat deflection temperature	D648		75	
	66 psi	190 °C	0.45 MPa	185 °C
	264 psi	100 °C	1.8 MPa	82 °C

Wear & Abrasion Resistance

	Pin on Disk	Thrust Washer
* Condition	1.3 MPa, 0.06 m/sec	0.4 MPa, 0.12 m/sec
Dynamic coefficient of Friction against self		0.17
Dynamic coefficient of Friction against steel		0.27
Wear factor against self		0.0010 mm ³ /N·km
Wear factor against steel		0.010 mm ³ /N·km
Taber abrasion 1kg load, CS-17 wheel	ASTM D1044	

Electrical Properties

	Test Method & Condition	Value
Dielectric Strength (DS)	ASTM D149	
	3 mm	16 kV/mm
	2 mm	19 kV/mm
Volume Resistivity (VR)	ASTM D257	10 ¹³ Ω·cm
Surface Resistivity (SR)	ASTM D257	10 ¹⁷ Ω /m ²
Dielectric constant at 60Hz	ASTM D150	6.1
Dissipation factor at 60Hz	ASTM D150	0.014

Injection Molding Processing Conditions

	Value
Pre-drying	Drying temperature
	80 °C
	Drying time
Temperature	3 ~ 4 hr
	Suggested max moisture
	0.20 %
	Nozzle temperature
	240 °C
	Zone 1 temperature
	230 °C
	Zone 2 temperature
	220 °C
	Zone 3 temperature
Pressure	215 °C
	Zone 4 temperature
	210 °C
Speed	Processing temperature
	225 ~ 240 °C
	Mold temperature
	60 ~ 80 °C
	Back pressure
	0.294 ~ 0.686 MPa
	Screw Speed
	50 ~ 100 rpm

* The data listed here is not for specification warranty, but typical value.

All products purchased from or supplied by Hyosung Chemical Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of loading. Values given above are simply references for representing typical level and do not expressly or impliedly guarantee anything. Neither should it be interpreted as specification limit nor sole criterion for part/tool design that is intended to have a legal binding effect. All other information, including that herein, supplied by Hyosung Chemical is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Hyosung Chemical makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Hyosung Chemical" refer to the collectivity of Hyosung Chemical engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Hyosung Chemical is the commitment of such individual company only.