

TECHNICAL DATA SHEET

Topilene® J346F**Polypropylene Block Copolymer**
For CPP Film Extrusion**Product Description**

Topilene® J346F is a specially designed polypropylene block copolymer that features very high impact strength and excellent optical properties. It is suitable for retort CPP film extrusion. **Topilene® J346F** complies with FDA 21 CFR 177.1520 and EU No 10/2011 for food contact.

Characteristics**Typical Application** Retort CPP film / Cast Film**Features** High Stiffness / High Impact Strength / Excellent Heat Resistance / Low Fisheye / Good Heat Seal Strength**Typical Properties**

Resin Properties	Method	Value	Unit
Melt Index(230°C, 2.16kg)	ASTM D1238	2.5	g/10min
Density	ASTM D792	0.9	g/cm ³
Tensile Strength at Yield	ASTM D638	300	kg/cm ²
Flexural Modulus	ASTM D790	13,300	kg/cm ²
Notched Izod Impact Strength(23°C)	ASTM D256	12	kg-cm/cm
Rockwell Hardness	ASTM D785	90	R-Scale
Heat Deflection Temperature	ASTM D648	110	°C
Vicat Softening Point	ASTM D1525	150	°C
Haze(40 µm CPP film)	ASTM D1003	69	%

The values listed above are typical values for reference purpose only and shall not be construed as specifications.

Storage and Handling

This product should be stored in dry condition at temperature below 40°C and protected from UV-light. When condensation is visible or can be expected, pre-drying is recommended. (Drying condition: 80~100°C/2~4hours at air circulated condition)

Disclaimer

All information, including product characteristics, applications and properties are for reference purpose only and shall not be construed as specifications. Before using this product, customers should carefully review the instructions for use of the product to determine whether the product is suitable for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of this product. HYOSUNG CHEMICAL CORPORATION assumes no legal responsibility or liability for the contents of this document. We reserve the right to change the contents of this document without prior notice. This document is copyrighted by HYOSUNG CHEMICAL CORPORATION. **Topilene®** is a registered trademark owned or used by HYOSUNG CHEMICAL CORPORATION.

Contacts

Head Office 235, Banpo-daero, Seocho-gu, Seoul, Korea 06578
Tel: +82-2-2146-5451~9 Fax: +82-2-2146-5428
Online www.hyosungchemical.com
www.topilene.com

**HYOSUNG CHEMICAL**