

# Luran S ECO 776SE BC40

Acrylonitrile Styrene Acrylate (ASA)

## TECHNICAL DATASHEET

### DESCRIPTION

Luran® S acrylonitrile styrene acrylate (ASA) polymers feature high surface quality and good impact strength including enhanced colour fastness. The products deliver superior long-term performance when exposed to UV irradiation and additionally provide excellent chemical resistance. Luran® S ECO 776SE is an extrusion grade providing enhanced impact strength and matte surface appearance for extruded sheets. Luran S ECO 776SE BC40 is an ISCC compliant product leading to a substitution of fossil source styrene with ISCC certified bio-attributed styrene.

### FEATURES

- Well extrudable
- Long-term property retention
- Low gloss
- UV resistance

### APPLICATIONS

- PVC capstock for sheets, sidings, roof tiles, gardening equipment
- Extruded sheets & profiles
- Sidings and deckings

| Property, Test Condition                                         | Standard    | Unit                    | Values |
|------------------------------------------------------------------|-------------|-------------------------|--------|
| <b>Sustainability Properties</b>                                 |             |                         |        |
| Carbon Footprint Reduction vs Fossil-Based (3rd party validated) | ISO 14044   | %                       | 53     |
| Attributed Content of ISCC-certified Bio-Circular Sources (min.) | -           | %                       | 40     |
| <b>Rheological Properties</b>                                    |             |                         |        |
| Melt Volume Rate 220 °C/10 kg                                    | ISO 1133    | cm <sup>3</sup> /10 min | 4      |
| <b>Mechanical Properties</b>                                     |             |                         |        |
| Charpy Notched Impact Strength, 23° C                            | ISO 179/1eA | kJ/m <sup>2</sup>       | 30     |
| Charpy Notched Impact Strength, -30 °C                           | ISO 179/1eA | kJ/m <sup>2</sup>       | 4      |
| Charpy Unnotched, 23 °C                                          | ISO 179/1eU | kJ/m <sup>2</sup>       | 260    |
| Tensile Modulus                                                  | ISO 527     | MPa                     | 2200   |
| Tensile Stress at Yield, 23 °C                                   | ISO 527     | MPa                     | 47     |
| Tensile Strain at Yield, 23 °C                                   | ISO 527     | %                       | 3.3    |
| Nominal Strain at Break, 23 °C                                   | ISO 527     | %                       | 12     |
| Flexural Modulus, 23 °C                                          | ISO 178     | MPa                     | 2000   |
| Flexural Strength, 23 °C                                         | ISO 178     | MPa                     | 65     |
| Hardness, Ball Indentation                                       | ISO 2039-1  | MPa                     | 70     |

# Luran S ECO 776SE BC40

Acrylonitrile Styrene Acrylate (ASA)

## TECHNICAL DATASHEET

| Property, Test Condition                                      | Standard        | Unit                 | Values    |
|---------------------------------------------------------------|-----------------|----------------------|-----------|
| <b>Thermal Properties</b>                                     |                 |                      |           |
| Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)           | ISO 306         | °C                   | 92        |
| Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)  | ISO 75          | °C                   | 96        |
| Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa) | ISO 75          | °C                   | 101       |
| Coefficient of Linear Thermal Expansion                       | ISO 11359       | 10 <sup>-6</sup> /°C | 80 - 110  |
| Thermal Conductivity                                          | ISO 22007-4     | W/(m K)              | 0.17      |
| <b>Other Properties</b>                                       |                 |                      |           |
| Density                                                       | ISO 1183        | kg/m <sup>3</sup>    | 1070      |
| Water Absorption, Saturated at 23 °C                          | ISO 62          | %                    | 1.65      |
| Moisture Absorption, Equilibrium 23 °C/50% RH                 | ISO 62          | %                    | 0.35      |
| Burning rate (US-FMVSS), 2.0 mm                               | ISO 3795        | mm/min               | 25        |
| UL94 rating at 1.5 mm thickness                               | IEC 60695-11-10 | -                    | HB        |
| <b>Processing</b>                                             |                 |                      |           |
| Melt Temperature Range                                        | ISO 294         | °C                   | 200 - 250 |
| Drying Temperature                                            | -               | °C                   | 80        |
| Drying Time                                                   | -               | h                    | 2 - 4     |

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

## SUPPLY FORM

Luran® S ECO is delivered in the form of cylindrical or spherical pellets. The bulk density of the pellets is from 0.55 to 0.65 g/cm<sup>3</sup>. Values may differ for special grades. Standard Packaging unit: 25 kg PE-bag on palette, shrunk or wrapped with PE film. In addition, delivery in larger units of up to 1000 kg (IBC = Intermediate Bulk Container) or silo trucks can be arranged. In dry areas with normal temperature control, Luran S pellets can be stored for relatively long periods of time without any change in mechanical properties. With unstable colors, however, storage over a number of years can give rise to some change in color. Under poor storage conditions, Luran S absorbs moisture, but this can be removed by drying.

## PRODUCT SAFETY

Contact us:  
[INSTY.infopoint.emea@ineos.com](mailto:INSTY.infopoint.emea@ineos.com)  
[www.ineos-styrolution.com](http://www.ineos-styrolution.com)

Page 2 of 3  
 Revision Date: 03/28/2023

## Luran S ECO 776SE BC40

Acrylonitrile Styrene Acrylate (ASA)

TECHNICAL  
DATASHEET

No adverse effects on the health of processing personnel have been observed where the products are correctly processed and the production areas are suitably ventilated. For styrene, alpha-methylstyrene, acrylonitrile, and butyl acrylate the maximum allowable workplace concentrations must be observed according to the pertaining national regulations. In Germany, the following limit values are valid TRGS 900 (Aug. 2004): styrene, MAK-value: 20 ml/m<sup>3</sup>; alpha-methylstyrene, MAK-value: 100 ml/m<sup>3</sup>; acrylonitrile, TRK-value: 3 ml/m<sup>3</sup>, and butyl acrylate, MAK-value: 2 ml/m<sup>3</sup> (1.7.2004). According to EU directive 67/548/EEC, Annex I (2001), acrylonitrile is classified as carcinogenic, category 2 ('substances which should be regarded as if they are carcinogenic to man'). Experience has shown that when Luran® S ECO is processed correctly with appropriate ventilation, the levels are far below the limits mentioned above. Inhalation of the vapors of degradation products which can arise on severe overheating of the materials or during purging out should be avoided. Further information can be found in the Luran S ECO safety data sheets.

## DISCLAIMER

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.