

Luran S KR2858G3

Acrylonitrile Styrene Acrylate (ASA)

TECHNICAL DATASHEET

DESCRIPTION

Luran® S KR2858G3 is a 15% glass fiber reinforced grade offering enhanced heat resistance and superior rigidity.

FEATURES

- Highest rigidity
- High heat resistance

APPLICATIONS

- Wind turbines
- Automotive guide plates

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	5
Mechanical Properties			
Tensile Modulus	ISO 527	MPa	6600
Tensile Stress at Break, 23 °C	ISO 527	MPa	110
Tensile Strain at Break, 23 °C	ISO 527	%	2.5
Flexural Strength, 23 °C	ISO 178	MPa	140
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	7
Charpy Notched Impact Strength, -30 °C	ISO 179/1eA	kJ/m ²	5
Charpy Unnotched Impact Strength, 23 °C	ISO 579	kJ/m ²	28
Charpy Unnotched Impact Strength, -30 °C	ISO 579	kJ/m ²	17
Hardness, Ball Indentation	ISO 2039-1	MPa	170
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	115
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	120
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	110
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	115
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	30
Other Properties			

Luran S KR2858G3

Acrylonitrile Styrene Acrylate (ASA)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Density	ISO 1183	kg/m ³	1180
Water Absorption, Saturated at 23 °C	ISO 62	%	1.42
Moisture Absorption, Equilibrium 23 °C/50% RH	ISO 62	%	0.3
Glass Fibre content	-	%	15
Processing			
Melt Temperature Range	ISO 294	°C	240 - 280
Mold Temperature Range	ISO 294	°C	40 - 95
Drying Temperature	-	°C	80
Drying Time	-	h	2 - 4
Molding shrinkage, free, longitudinal	-	%	0.4

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

SUPPLY FORM

Luran® S is delivered in the form of cylindrical or spherical pellets. The bulk density of the pellets is from 0.55 to 0.65 g/cm³. Values may differ for special grades. Standard Packaging unit: 25 kg PE-bag on palette, shrunk or wrapped with PE film. In addition, delivery in larger units of up to 1000 kg (IBC = Intermediate Bulk Container) or silo trucks can be arranged. In dry areas with normal temperature control, Luran S pellets can be stored for relatively long periods of time without any change in mechanical properties. With unstable colors, however, storage over a number of years can give rise to some change in color. Under poor storage conditions, Luran S absorbs moisture, but this can be removed by drying.

PRODUCT SAFETY

No adverse effects on the health of processing personnel have been observed where the products are correctly processed and the production areas are suitably ventilated. For styrene, alpha-methylstyrene, acrylonitrile, and butyl acrylate the maximum allowable workplace concentrations must be observed according to the pertaining national regulations. In Germany, the following limit values are valid TRGS 900 (Aug. 2004): styrene, MAK-value: 20 ml/m³; alpha-methylstyrene, MAK-value: 100 ml/m³; acrylonitrile, TRK-value: 3 ml/m³, and butyl acrylate, MAK-value: 2 ml/m³ (1.7.2004). According to EU directive 67/548/EEC, Annex I (2001), acrylonitrile is classified as carcinogenic, category 2 ("substances which should be regarded as if they are carcinogenic to man"). Experience has shown that when Luran® SC is processed correctly with appropriate ventilation, the levels are far below the limits mentioned above. Inhalation of the vapors of degradation products which can arise on severe overheating of the materials or during purging out should be avoided. Further information can be found in the Luran SC safety data sheets.

DISCLAIMER

Contact us:
Infopoint.emea@styrolution.com
www.ineos-styrolution.com

Page 2 of 3
Revision Date: 12/12/2018

INEOS
STYROLUTION**Luran S KR2858G3**

Acrylonitrile Styrene Acrylate (ASA)

**TECHNICAL
DATASHEET**

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.