

Lustran 446

Please Select

TECHNICAL
DATASHEET

DESCRIPTION

Lustran® 446 resin is a high-impact grade of ABS (Acrylonitrile Butadiene Styrene). This automotive injection molding grade provides a good balance of mechanical properties and impact strength for substrate applications.

FEATURES

- SAE J1685: ABS 0111
- High Impact Strength
- Good Balance of Properties

APPLICATIONS

- Non appearance structural components for truck, bus and automotive

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 230 °C/3.8 kg	ISO 1133	g/10 min	4
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm³/10 min	13
Mechanical Properties			
Izod Notched Impact Strength, 23 °C (73 °F)	ASTM D 256	kJ/m²	30
Izod Notched Impact Strength, -40 °C (-40 °F)	ASTM D 256	kJ/m²	5.1
Tensile Stress at Yield, 23 °C	ISO 527	MPa	44
Flexural Modulus, 23 °C	ISO 178	MPa	2540
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	97
Processing			
Drying Temperature	-	°C	80

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

SUPPLY FORM

Lustran® ABS (Acrylonitrile Butadiene Styrene) resins are available in bulk railcar, bulk truckload and 726kg box quantities.

**INEOS
STYROLUTION****Lustran 446**

Please Select

**TECHNICAL
DATASHEET****REGULATORY COMPLIANCE**

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

PROCESSING

A reciprocating screw injection molding machine is preferred. A general-purpose screw with a 2.5:1 compression ratio is suggested. A minimum L/D ratio of 20:1 will ensure melt homogeneity. For best part quality, use the lower range of the recommended melt temperature with minimum barrel residence time. To avoid excessive residence time in the barrel, volume and weight of the shot should be balanced against barrel capacity and injection stroke. A shot weight-to-machine capacity ratio of 0.5-0.75 is recommended. A mold temperature of 110°-150°F (45°-65°C) is recommended for development of maximum gloss and strength, with the hotter end of this range preferred.

PRODUCT SAFETY

Safety Data Sheets and product labels provide information concerning the health and safety precautions that must be observed when handling the Styrolution products mentioned in this publication. No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile, alpha-methyl styrene, maleic anhydride and 1, 3-butadiene, the maximum allowable workplace concentrations must be observed according to current local and federal regulations. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. This information is available in safety data sheets and on product labels. If there are questions or concerns, consult your Styrolution representative or contact the Product Safety and Regulatory Affairs Department at Styrolution.

DISCLAIMER

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.