

INEOS STYROLUTION

Lustran 556

Acrylonitrile Butadiene Styrene (ABS)

TECHNICAL DATASHEET

DESCRIPTION

Lustran® 556 is a very low-gloss, medium impact ABS (acrylonitrile butadiene styrene) designed for extrusion/thermoforming applications. It provides a consistent low-gloss appearance in both mono-layer and co-extruded applications.

FEATURES

- Very low gloss
- Medium impact strength
- Ease of coloring
- UL 94 HB rated

APPLICATIONS

- Motor vehicle dashboards
- Interior panels
- Interior trim

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 220 °C/10 kg	ASTM D 1238	g/10 min	6
Mechanical Properties			
Izod Notched Impact Strength, 23 °C (73 °F)	ASTM D 256	ft-lb/in	2
Izod Notched Impact Strength, -18 °C (0 °F)	ASTM D 256	ft-lb/in	1.3
Izod Notched Impact Strength, -40 °C (-40 °F)	ASTM D 256	ft-lb/in	1
Instrumented Dart Impact (total energy)	ASTM D 3763	in-lbs	264
Instrumented Dart Impact (Peak force)	ASTM D 3763	in-lbs	228
Tensile Stress at Break, 23 °C	ASTM D 638	psi	3200
Tensile Stress at Yield, 23 °C	ASTM D 638	psi	2800
Tensile Modulus	ASTM D 638	psi x 10 ³	220
Thermal Properties			
DTUL @ 264 psi - Unannealed	ASTM D 648	°F	187
DTUL @ 66 psi - Unannealed	ASTM D 648	°F	205
Coefficient of Linear Thermal Expansion	ASTM D 696	10 ⁻⁴ /°F	0.54
Other Properties			
Density	ASTM D 792	lb/in ³	1.06
Processing			

Contact us:
 Phone +1 866 890 6353
INSTY.infopoint.america@ineos.com
www.ineos-styrolution.com

Page 1 of 2
 Revision Date: 02/17/21

**INEOS
STYROLUTION****Lustran 556**

Acrylonitrile Butadiene Styrene (ABS)

**TECHNICAL
DATASHEET**

Property, Test Condition	Standard	Unit	Values
Linear Mold Shrinkage	ASTM D 955	in/in	0.004 - 0.006
Drying Temperature	-	°F	175
Drying Time	-	h	2 - 4

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.
Please consult our local sales or technical representatives for details.

SUPPLY FORM

Lustran® ABS (Acrylonitrile Butadiene Styrene) resins are available in bulk railcar, bulk truckload and 726kg box quantities.

REGULATORY COMPLIANCE

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

PROCESSING

To obtain an optimum balance of appearance and mechanical properties, the extruder profile should be set to deliver polymer at a melt temperature between 420° and 480°F (215° and 249°C). A barrel temperature of 420°-465°F (215-240°C) is recommended.

PRODUCT SAFETY

Safety Data Sheets and product labels provide information concerning the health and safety precautions that must be observed when handling the Styrolution products mentioned in this publication. No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile, alpha-methyl styrene, maleic anhydride and 1, 3-butadiene, the maximum allowable workplace concentrations must be observed according to current local and federal regulations. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. This information is available in safety data sheets and on product labels. If there are questions or concerns, consult your Styrolution representative or contact the Product Safety and Regulatory Affairs Department at Styrolution.

DISCLAIMER

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.