

Lustran SAN DN77

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

DESCRIPTION

SAN resin supplied in natural color for use in compounding applications

APPLICATIONS

- Compounding

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Flow Rate, 230 °C/3.8 kg	ASTM D 1238	g/10 min	14
Melt Volume Rate 220 °C/10 kg	ASTM D 1238	cm³/10 min	34
Mechanical Properties			
Izod Unnotched Impact Strength, 23 °C	ASTM D 256	ft-lb/in	6
Tensile Stress at Break, 23 °C	ASTM D 638	psi	10000
Flexural Strength, 23 °C	ASTM D 790		11000
Flexural Modulus, 23 °C	ASTM D 790	psi x 10³	500
Thermal Properties			
Vicat Softening Temperature, B/1 (120 °C/h, 10N)	ASTM D 1525	°F	109
Other Properties			
Density (ASTM)	ASTM D 792	g/cm³	1.08

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

SUPPLY FORM

Lustran SAN styrene acrylonitrile resins are available in bulk railcar, bulk truckload and 726kg box quantities.

REGULATORY COMPLIANCE

Please refer to Styrolution web site or contact Styrolution Technical Service for further information.

Contact us:

Phone +1 866 890 6353

Infopoint.americas@styrolution.com

www.ineos-styrolution.com

Page 1 of 2

Revision Date: 01/17/16

Lustran SAN DN77

Styrene Acrylonitrile (SAN)

TECHNICAL DATASHEET

PRODUCT SAFETY

Safety Data Sheets and product labels provide information concerning the health and safety precautions that must be observed when handling the Styrolution products mentioned in this publication. No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile, alpha-methyl styrene, maleic anhydride and 1, 3-butadiene, the maximum allowable workplace concentrations must be observed according to current local and federal regulations. Before working with any of these products, you must read and become familiar with the available information on their hazards, proper use, and handling. This cannot be overemphasized. This information is available in safety data sheets and on product labels. If there are questions or concerns, consult your Styrolution representative or contact the Product Safety and Regulatory Affairs Department at Styrolution.

DISCLAIMER

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.