

INEOS STYROLUTION

Styrolux 656C

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

DESCRIPTION

Styrolux® 656C is a clear styrene-butadiene copolymer (SBC) with enhanced flow properties. It is used almost exclusively for injection molding of rigid, tough parts requiring highest levels of clarity and surface gloss. Styrolux® 656C is sterilizable by gamma-rays and offers good hinge properties.

FEATURES

- Tough and stiff grade
- Enhanced flowability
- High clarity

APPLICATIONS

- Moulded containers and bottles
- Toys
- Displays
- Appliance housings
- Medical devices
- Garment hangers

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm ³ /10 min	16
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	3
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	2
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m ²	2
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m ²	25
Tensile Stress at Yield, 23 °C	ISO 527	MPa	35
Tensile Strain at Yield, 23 °C	ISO 527	%	2.4
Nominal Strain at Break, 23 °C	ISO 527	%	20
Tensile Modulus	ISO 527	MPa	1800
Tensile Creep Modulus (1000h)	ISO 899	MPa	1050
Tensile Creep Modulus (1h)	ISO 899	MPa	1550
Flexural Strength, 23 °C	ISO 178	MPa	48
Flexural Modulus, 23 °C	ISO 178	MPa	1900
Flexural Stress at 5% Deflection	-	MPa	48

Contact us:
INSTY.infopoint.emea@ineos.com
www.ineos-styrolution.com

Page 1 of 3
Revision Date: 04/30/2020

Styrolux 656C

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Hardness, Shore D	ISO 868	-	72
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	63
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	85
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	59
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	73
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	60 - 90
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.579
Light Transmission at 550 nm	ASTM D 1003	%	90
Haze	ASTM D 1003	%	< 1.5
Other Properties			
Density	ISO 1183	kg/m ³	1020
Water Absorption, Saturated at 23 °C	ISO 62	%	0.07
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1
Mold Temperature Range	ISO 294	°C	30 - 50
Melt Temperature Range	ISO 294	°C	180 - 250

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities.

Please consult our local sales or technical representatives for details.

SUPPLY FORM

Styrolux is supplied in pellet form and should be kept in its original containers in cool, dry place. Avoid direct exposure to sunlight. Styrolux® can be stored in silos at temperatures well below 45 °C.

PRODUCT SAFETY

During processing of Styrolux® small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well

Styrolux 656C

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

ventilated workplaces - that is where five to eight air changes per hour are made. For safety information please refer to our Material Safety Data Sheet for this product.

DISCLAIMER

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.