

INEOS
STYROLUTION**Styrolux 693D**

Styrene Butadiene Copolymer (SBC)

**TECHNICAL
DATASHEET****DESCRIPTION**

Styrolux® 693D is a clear styrene-butadiene copolymer (SBC) with a well balanced combination of toughness and clarity. Styrolux 693D is mainly used for thermoformed articles, especially in blends with general-purpose polystyrene. Styrolux® 693D contains a microcrystalline wax which acts as an antiblock providing processing benefits but decreases the printability.

FEATURES

- Good clarity
- Very high toughness
- Enhanced GPPS blend capability

APPLICATIONS

- Food and non-food packaging
- Blown film
- Cups for cold beverages
- Thermoformed transparent containers
- Lids & Boxes

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate, 200 °C/5 kg	ISO 1133	cm³/10 min	12
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m²	3.5
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m²	2.5
Charpy Notched Impact Strength, 23° C	ISO 179/1eA	kJ/m²	5
Charpy Unnotched, 23 °C	ISO 179/1eU	kJ/m²	> 80
Tensile Stress at Yield, 23 °C	ISO 527	MPa	22
Tensile Strain at Yield, 23 °C	ISO 527	%	2.2
Nominal Strain at Break, 23 °C	ISO 527	%	260
Flexural Strength, 23 °C	ISO 178	MPa	32
Flexural Modulus, 23 °C	ISO 178	MPa	1400
Hardness, Shore D	ISO 868	-	64
Tensile Modulus	ISO 527	MPa	1230
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50N, 50 °C/h)	ISO 306	°C	48

Styrolux 693D

Styrene Butadiene Copolymer (SBC)

TECHNICAL DATASHEET

Property, Test Condition	Standard	Unit	Values
Vicat Softening Temperature, VST/A/50 (10N, 50 °C/h)	ISO 306	°C	76
Heat Deflection Temperature A; (annealed 4 h/80 °C; 1.8 MPa)	ISO 75	°C	59
Heat Deflection Temperature B; (annealed 4 h/80 °C; 0.45 MPa)	ISO 75	°C	72
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	60 - 90
Optical Properties			
Refractive Index, Sodium D Line	ISO 489	-	1.57
Light Transmission at 550 nm	ASTM D 1003	%	89
Haze	ASTM D 1003	%	< 2
Other Properties			
Density	ISO 1183	kg/m ³	1010
Water Absorption, Saturated at 23 °C	ISO 62	%	0.07
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.3 - 1
Melt Temperature Range	ISO 294	°C	180 - 250
Mold Temperature Range	ISO 294	°C	20 - 40

Typical values for uncolored products

Please note that all processing data stated are only indicative and may vary depending on the individual processing complexities. Please consult our local sales or technical representatives for details.

SUPPLY FORM

Styrolux is supplied in pellet form and should be kept in its original containers in cool, dry place. Avoid direct exposure to sunlight. Styrolux® can be stored in silos at temperatures well below 45 °C.

PRODUCT SAFETY

During processing of Styrolux® small quantities of styrene monomer may be released into the atmosphere. At styrene vapor concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces - that is where five to eight air changes per hour are made. For safety information please refer to our Material Safety Data Sheet for this product.

DISCLAIMER

Contact us:
 INSTY.infopoint.emea@ineos.com
www.ineos-styrolution.com

Page 2 of 3
 Revision Date: 09/05/16

INEOS
STYROLUTION**Styrolux 693D**

Styrene Butadiene Copolymer (SBC)

**TECHNICAL
DATASHEET**

The above mentioned data are accurate to the best of our knowledge. They are based upon reputable labs and industry standard testing methods. These are only typical values and actual product specification may deviate at industrial range. Therefore, no data in this technical data sheet shall constitute a warranty or representation regarding product features, fitness of the product for a specific purpose or application or its processability. INEOS Styrolution disclaims all liability in connection therewith. The customer himself is required to verify whether or not the product is suitable for the further processing or application intended and whether or not the product complies with the relevant statutory requirements. Unless explicitly and individually otherwise agreed in writing, INEOS Styrolution's sole and exclusive liability with respect to its products is set forth in INEOS Styrolution's General Terms and Conditions for Sale.