



Eltex® A 4040

Product Technical Information

Eltex® A 4040 is a medium-density supplies as a non pigmented natural pellet for the production of PE-Xb compounds using two-step process or for the manufacture of PEX pipes using a simple-step process.

Characteristics

- Natural polyethylene for silane PE-Xb processes

Applications

- Hot & cold water
- All classes of application in accordance with EN ISO 15875 and ISO 10508

Properties	Test Method	Value	Units
Physical			
Density (pigmented)	ISO 1183/A	944	kg/m ³
Melt Flow Rate (2.16 kg/190°C, Condition D)	ISO 1133	3.5	g/10min
Mechanical			
Tensile Strength @ Yield (23°C @ 50 mm/min)	ISO 527-2	21	MPa
Tensile Elongation @ Break (23°C @ 50 mm/min)	ISO 527-2	> 350	%
Tensile Modulus (23°C @ 1 mm/min)	ISO 527-2	900	MPa
Thermal			
VICAT Softening Point (1 kg)	ISO 306	123	°C

The values given are typical values measured on the product. These values should not be considered as specifications.

September, 2006

Published by
INEOS Polyolefins



Eltex® A 4040

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@innovene.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website <http://techservice.innovene.com>. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of their materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.

September, 2006

Published by
INEOS Polyolefins