



22D730

Product Technical Information

LDPE for Blown film

22D730 is an autoclave, low density polyethylene grade for film application. 22D730 is developed to give an extra strong film for heavy duty film applications such as sacks and pallet shrink.

Applications

22D730 is intended for applications such as

- Heavy duty bags
- Shrink films
- Liners
- Construction and agricultural films

Properties	Test Method	Value	Units
Physical			
Melt flow rate (190°C/2.16 kg)	ISO 1133	0.3	g/10 min
Density	ISO 1183	922	kg/m ³
Melting temperature	ISO 11357/03	110	°C
Vicat softening temperature	ISO 306	96	°C
Additive free			
Film*			
Tensile strength MD/TD	ISO 527-3	25/23	MPa
Tensile strain @ break MD/TD	ISO 527-3	400/600	%
Tensile modulus (0.05-1.05%) MD/TD	ASTM D 882-A	170/180	MPa
Coefficient of friction Dynamic	ISO 8295	> 0.5	-
Dart drop	ISO 7785/1	450	g
Haze	ASTM D1003	15	%
Gloss (45°)	ASTM D2457	43	% ₀₀

- Data should not used for specification work

* Film properties are measured on a 125µm film sample produced on a 60mm W&H extruder with IBC cooling at BUR=12,5. MD = machine direction, TD = transverse direction

February, 2008

Published by
INEOS Polyolefins



22D730

Storage and Handling

22D730 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation which results in odour generation and colour changes, and can have negative effects on the physical properties of the product.

Processing guidelines

22D730 is easily processed on conventional extruders.

Recommended melt temperature range is from 170°C to 200°C. Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be sought for each production line.

With suitable equipment 22D730 can be drawn down to 70-75 micron.

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@innovene.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolyolefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS POLYOLEFINS endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS POLYOLEFINS is accurate and up to date, no representation or warranty, express or implied is made by INEOS POLYOLEFINS as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS POLYOLEFINS are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS POLYOLEFINS is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS POLYOLEFINS materials are suitable for the particular purpose intended and INEOS POLYOLEFINS shall not be responsible for any loss or damage caused by misuse of INEOS POLYOLEFINS products. To the maximum extent permitted by law, INEOS POLYOLEFINS accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS POLYOLEFINS materials or the use of INEOS POLYOLEFINS materials in conjunction with such other materials.

February, 2008

Published by
INEOS Polyolefins