



Rigidex® P 450-HP60

Product Technical Information

Rigidex® P 450-HP60 is a nucleated and antistatic high flow high impact copolymer specifically designed for very fast cycling, thin walled injection moulding applications. The Rigidex® P series of polypropylene resins are manufactured using the latest catalyst/process developments on Innovene P gas phase technology. As a result, they offer an industry leading balance between fluidity, rigidity and impact resistance. New nucleating technology leads to higher isotropy and subsequently lower warpage of the final objects.

Applications

- Very Thin Walled Technical Mouldings
- Yellow fat containers
- Housewares

Benefits and Features

- Very good impact, even below 0°C
- Low warpage
- Very high flowability
- Very short cycle time
- Antistatic

Properties		Test Methods	Values	Units
Physical				
Melt Flow Rate	230°C/2.16kg	ISO 1133	60	g/10min
Mechanical				
Flexural Modulus	@23°C	ISO 178	1400	MPa
Izod impact strength, notched	@+23°C	ISO 180/1A	6.2	kJ/m²
	@-20°C	ISO 180/1A	4.2	kJ/m²
Thermal				
HDT	@0.45 MPa	ISO 75/B	105	°C

- Data should not be used for specification work

October, 2009

Published by
INEOS Olefins & Polymers Europe



Rigidex® P 450-HP60

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, send an email to psnohreg@ineos.com. Unless specifically indicated, the products mentioned herein are not suitable for applications in the medical or pharmaceutical sector.

Health and Safety Information

The product described herein may require precautions in handling. The available product health and safety information for this material is contained in the Material Safety Data Sheet (MSDS) that may be obtained from the website www.ineospolylefins.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

Exclusion of Liability

Although INEOS O&P Europe endeavours to ensure that all information and advice relating to our materials or other materials howsoever provided to you by INEOS O&P Europe is accurate and up to date, no representation or warranty, express or implied is made by INEOS O&P Europe as to its accuracy or completeness. All such information and advice is provided in good faith and INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action you may take as a result of relying on such information or advice or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

In addition data and numerical results howsoever provided to you by INEOS O&P Europe are given in good faith and are general in nature. Data and numerical results are not and shall not be regarded as specifications and as such INEOS O&P Europe is not, to the maximum extent permitted by law, liable for any action that you take as a result of relying on such data and results or for any loss or damage, including any consequential loss, suffered by you as a result of taking such action.

It remains at all times your responsibility to ensure that INEOS O&P Europe materials are suitable for the particular purpose intended and INEOS O&P Europe shall not be responsible for any loss or damage caused by misuse of INEOS O&P Europe products. To the maximum extent permitted by law, INEOS O&P Europe accepts no liability whatsoever arising out of the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS O&P Europe materials or the use of INEOS O&P Europe materials in conjunction with such other materials.

October, 2009

Published by
INEOS Olefins & Polymers Europe