

INOVYN™ & BIOVYN™PVC resins for Paste - Main applications

Grade	BIOVYN™ grades	K value ISO 1628-2	Low fog	Viscosity	Rheology	Spread coating										Spray coating	Moulding		Dipping		Special applications			Characteristics				
						Artificial leather		Flooring				Technical Textiles		Wall covering			Car underbody coating & sealants	Rotational	Other Moulding	Gloves		Other Dipping	PUR Sealants		Printing	Cap closures		
						Compact Foam	Wear layer	Base & impregnation layer	Mechanical foam	Chemical foam	Carpet backing	Base coat	Top coat	Compact Foam	Coil coating	Supported				Unsupported								
Dispersion resins																												
P602	x	59		medium	N	x	x	x	x		x	x		x	x			x									Fast gelation	
360NA		60		low	N	x	x	x	x		x	x			x	x			x									Fast gelation
367NC	x	67	Yes	low	N	x	x	x	x						x	x			x									Low fog properties
367NF		67		low	N	x	x	x	x		x	x			x	x			x									Multipurpose
367NK		67		low-medium	N	x			x					x		x	x		x					x		x		Excellent foaming properties
P11	x	68		low	N	x	x	x	x	x	x	x	x	x		x	x			x								Multipurpose
P15	x	68		low	N	x		x	x					x														Excellent foaming properties
P1510	x	68		low	N						x	x	x	x									x		x			Very fine particles
P682	x	68		medium	N		x			x				x				x	x				x					Excellent foaming properties
P1412	x	69		medium	D	x		x			x	x			x			x	x				x	x		x		Excellent outdoor behaviour, excellent air release
P2170	x	69		low	N				x	x		x	x	x				x										High filler acceptance
370HK		69.5		high	PS	x	x									x							x					Highly thixotropic
370HM		69.5		high	PS	x	x									x							x					Highly thixotropic
370HD	x	70	Yes	high	PS	x	x					x				x							x					Highly plasticised applications, low fog
P709	x	70		medium-high	PS	x	x					x				x							x					Excellent foams, viscosity modifier
P737	x	71		high	D													x		x			x					Benchmark for supported gloves
372HA	x	71.5		medium-high	PS		x					x				x									x			Low water uptake
372LD		72		low	D																			x		x		For special food sealants
372NF		72		low	N	x	x	x	x		x		x					x	x				x			x		Multipurpose
373MC	x	73		medium	N	x	x					x	x					x	x				x	x				Benchmark for polyurethane sealants
373MH	x	73	Yes	medium	N	x	x						x															Low fog, car interiors
373ND	x	73	Yes	low	N	x	x					x	x															Excellent air release, car interiors

N: newtonian; D: dilatant; PS: pseudoplastic

Grade	BIOVYN™ grades	K value ISO1628-2	Low fog	Viscosity	Rheology	Spread coating										Spray coating	Moulding	Dipping		Special applications		Characteristics							
						Artificial leather		Flooring				Technical Textiles		Wall covering				Car underbody coating & sealants	Rotational	Other Moulding	Gloves		Other Dipping	PUR Sealants	Printing	Cap closures			
						Compact Foam	Wear layer	Base & impregnation layer	Mechanical foam	Chemical foam	Carpet backing	Base coat	Top coat	Compact	Foam	Coil coating	Supported				Unsupported								
374MB	x	74		medium	PS	x	x					x	x			x	x	x			x			x	Multipurpose, good thermal stability				
375MD	x	75	Yes	medium-high	PS	x	x					x	x													Excellent thermal stability, car interiors			
376NB	x	76		low	N	x		x				x	x				x	x			x					Matt finish, excellent air release			
382NG		82		low	N	x		x				x														Matt finish, very low viscosity			
P1482	x	82		low	N	x		x				x												x		Excellent mechanical properties & air release			
Special applications																													
370SK		69.5	Recommended applications: rigid PVC / Isocyanate foams																				Excellent mechanical properties						
172SD		72	Recommended application: battery separators																				Free-flowing, excellent sintering behaviour						
Extender Homopolymers																													
266EF	x	66	Yes				x	x	x	x	x	x	x	x	x	x	x	x	x			x			x	Excellent mechanical properties, matt finish			
266UF	x	66	Yes				x	x	x				x	x	x	x	x								x	Excellent mechanical properties, fine version			
Extender Copolymers																													
560SC	x	60	Yes									x					x									Fast gelation (10%VAc)			
PVC latexes																													
068SA		68	Recommended applications: water-based inks, varnishes, lacquers																				High mechanical stability						
072GA		71.5	Recommended applications: water-based inks, varnishes, lacquers																				Standard version						

N: newtonian; D: dilatant; PS: pseudoplastic