

INOVYN™ & BIOVYN™PVC resins for Paste - Main applications

Grade	BIOVYN™ grades	K value ISO 1628-2	Low fog	Viscosity	Rheology	Spread coating										Spray coating	Moulding		Dipping		Special applications			Characteristics		
						Artificial leather		Flooring				Technical Textiles		Wall covering			Car underbody coating & sealants	Rotational	Other Moulding	Gloves		Other Dipping	PUR Sealants		Printing	Cap closures
						Compact Foam	Wear layer	Base & impregnation layer	Mechanical foam	Chemical foam	Carpet backing	Base coat	Top coat	Compact Foam	Coil coating	Supported				Unsupported						
Dispersion resins																										
P602	x	59		medium	N	x	x	x	x	x		x	x			x	x			x						Fast gelation
360NA		60		low	N	x	x		x	x		x	x			x	x			x						Fast gelation
367NC	x	67	Yes	low	N	x	x	x	x							x	x			x						Low fog properties
367NF		67		low	N	x	x		x	x		x	x			x	x			x						Multipurpose
367NK		67		low-medium	N	x			x				x		x	x	x			x			x			Excellent foaming properties
P11	x	68		low	N	x	x		x	x	x	x	x	x		x	x			x						Multipurpose
P15	x	68		low	N	x		x		x				x												Excellent foaming properties
P1510	x	68		low	N							x	x	x	x							x		x		Very fine particles
P682	x	68		medium	N		x			x				x			x	x			x					Excellent foaming properties
P1412	x	69		medium	D	x		x				x	x		x		x	x			x	x			x	Excellent outdoor behaviour, excellent air release
P2170	x	69		low	N				x	x		x	x	x			x									High filler acceptance
370HK		69.5		high	PS	x	x									x					x					Highly thixotropic
370HM		69.5		high	PS	x	x									x						x				Highly thixotropic
370HD	x	70	Yes	high	PS	x	x					x				x					x					Highly plasticised applications, low fog
P709	x	70		medium-high	PS	x	x					x				x						x				Excellent foams, viscosity modifier
P737	x	71		high	D												x		x		x					Benchmark for supported gloves
372HA	x	71.5		medium-high	PS		x					x				x							x			Low water uptake
372LD		72		low	D																	x			x	For special food sealants
372NF		72		low	N	x	x	x	x		x		x	x				x	x			x			x	Multipurpose
373MC	x	73		medium	N	x	x					x	x					x	x			x	x			Benchmark for polyurethane sealants
373MH	x	73	Yes	medium	N	x	x						x													Low fog, car interiors
373ND	x	73	Yes	low	N	x	x					x	x													Excellent air release, car interiors

N: newtonian; D: dilatant; PS: pseudoplastic

Grade	BIOVYN™ grades	K value ISO1628-2	Low fog	Viscosity	Rheology	Spread coating										Spray coating	Moulding	Dipping		Special applications		Characteristics						
						Artificial leather		Flooring				Technical Textiles		Wall covering				Car underbody coating & sealants	Rotational	Other Moulding	Gloves		Other Dipping	PUR Sealants	Printing	Cap closures		
						Compact Foam	Wear layer	Base & impregnation layer	Mechanical foam	Chemical foam	Carpet backing	Base coat	Top coat	Compact	Foam	Coil coating	Supported				Unsupported							
374MB	x	74		medium	PS	x	x					x	x			x	x	x			x			x	Multipurpose, good thermal stability			
375MD	x	75	Yes	medium-high	PS	x	x					x	x													Excellent thermal stability, car interiors		
376NB	x	76		low	N	x		x				x	x				x	x			x					Matt finish, excellent air release		
382NG		82		low	N	x		x				x														Matt finish, very low viscosity		
P1482	x	82		low	N	x		x				x												x		Excellent mechanical properties & air release		
Special applications																												
370SK		69.5	Recommended applications: rigid PVC / Isocyanate foams																								Excellent mechanical properties	
172SD		72	Recommended application: battery separators																								Free-flowing, excellent sintering behaviour	
Extender Homopolymers																												
266EF	x	66	Yes				x	x	x	x	x	x	x	x	x	x	x	x	x			x			x	Excellent mechanical properties, matt finish		
266UF	x	66	Yes				x	x	x				x	x	x	x	x								x	Excellent mechanical properties, fine version		
Extender Copolymers																												
560SC	x	60	Yes									x					x									Fast gelation (10%VAc)		
PVC latexes																												
068SA		68	Recommended applications: water-based inks, varnishes, lacquers																								High mechanical stability	
072GA		71.5	Recommended applications: water-based inks, varnishes, lacquers																								Standard version	

N: newtonian; D: dilatant; PS: pseudoplastic