



1111NXTA8

Polypropylene Compound

Description:

1111NXTA8 is a PP Homopolymer with 40% talcum filler for injection molding process, medium melt flow, high flexural modulus and high heat resistance. It is suitable for auto parts and electrical appliances.

Physical Properties:	Method	Unit	Value
Melt Flow Index (2.16 kg/230°C)	ASTM D1238	g/10min.	10.0
Density	ASTM D792	g/cm ³	1.26
Izod Notched Impact (23°C)	ASTM D256	Kg-cm/cm ²	2.2
Tensile Strength at Yield (23°C)	ASTM D638	kg/cm ²	365
Elongation at Break (23°C)	ASTM D638	%	4
Flexural Strength at Yield (23°C)	ASTM D790	kg/cm ²	560
Flexural Modulus (23°C)	ASTM D790	×10 ⁴ kg/cm ²	7.5
Rockwell Hardness (23°C)	ASTM D785	R-Scale	101
Heat Distortion Temperature (4.6 kg/cm ²)	ASTM D648	°C	147
Flammability	UL-94	-	HB (1.5)

Processing Technique

Drying Temperature: 80-85°C, 2-3 hrs

Processing Temperature: 190-240°C

****However, the actual processing conditions depend on mold design, power of machine, screw configurations and other environments.****

Remark: The values presented on the above are typical laboratory average, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.

Product Data sheet



บริษัท ไออาร์พีซี จำกัด (มหาชน)

555/2 ถนนวิภาวดีรังสิต อาคาร บี ชั้น 6 ถนนวิภาวดีรังสิต แขวงจตุจักร เขตจตุจักร กรุงเทพฯ 10900 โทร. +66(0)2649-7000, 66(0)2649-7777 แฟกซ์: +66(0)2649-7002

IRPC Public Company Limited

555/2 Energy Complex Building B, 6th Floor, Vibhavadi Rangsit Road, Chatuchak, Bangkok 10900 THAILAND. TEL: +66(0)2649-7000, 66(0)2649-7777 FAX: +66(0)2649-7002 www.irpc.co.th, www.irpcmarket.com

REV. 20110701