



HDPE made via Spherilene Process



Product data sheet **526H1**

526H1 is a HDPE copolymer for rigid blown film, with high molecular weight, and broad molecular weight distribution. 526H1 is well suited for applications requiring the best compromise between a good processability and outstanding film stiffness.

HDPE:526H1

Density: 0.952

MFI: 0.15(190C/5kg)

Features



- HDPE copolymer for rigid blown film
- high molecular weight and broad molecular weight distribution.
- best compromise between a good processability and outstanding film stiffness

Applications



- Film grade

Additives



- Grade under final development, to be industrialised.

94

Material properties (This data are typical values and are not to be construed as product specifications.)

Resin properties	Unit	Typical values	ASTM Method
Melt Flow rate (190 °C/5Kg)	(g/10')	0.15	D 1238
MFRs ratio (F/P)	(g/10')	>20	D 1238
Density	(g/ml)	0.952	D 1505
Physical properties @			
Tensile modulus, MD, (sec.2%)	(MPa)	900	D 882
Tensile modulus, TD, (sec.2%)	(MPa)	800	D 882
Tensile strenght at yield, MD	(MPa)	50	D 882
Tensile strenght at yield, TD	(MPa)	30	D 882
Elongation at break, MD	(%)	300	D 882
Elongation at break, TD	(%)	> 700	D 882
Dan impact resistance	(g)	70	D 1709/A
Tear propagation, MD	(g)	250	D 1004
Tear propagation TD	(g)	410	D 1004

@ On blown film, 15 µ, on a 80 mm industrial line.