



## HDPE made via Hostalen Process



### Product data sheet **HF7740F**

- Stretched film and tapes for production of high-strength knitted and wover.

**HDPE: HF7740F**

**Density: 0.944**

**MFI: 1.8**

#### Features



- Butene copolymer
- Excellent mechanical properties
- Excellent puncture resistance
- High impact strength

#### Applications



- Stretched tape (raffia)

#### Additives



- Antioxidant/Process stabilizer
- Lubricant (processing aid)/acid scavenger

### Material properties (This data are typical values and are not to be construed as product specifications.)

118

| Test/Composition | Typical Value | Unit              | Method   |
|------------------|---------------|-------------------|----------|
| Density          | 0.944         | g/cm <sup>3</sup> | ISO 1183 |
| Fish Eye Note    | ≤ 4           | note              | internal |
| FRR 21.6/5       | 15            |                   |          |
| MFR 190° /21.6   | 27            | g/10min           | ISO1133  |
| MFR190° /5       | 1.8           | g/10min           | ISO1133  |

- Test specimen from compression moulded sheet at 23°C.

- FRR values are statistical and calculated by dividing MFR values.

- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .