



HDPE made via Hostalen Process



Product data sheet **HM9445HT**

For blown films with paper like quality Suitable for counter bags, carrier bags and wrapping films, excellent processing.

HDPE: HM9445HT

Density: 0.944

MFI: 0.18

Features



- High tenacity film grade.

Applications



- blown
- Film

Additives



- Antioxidant / Process stabilizer
- Lubricant (processing aid) / acid scavenger

Material properties (This data are typical values and are not to be construed as product specifications.)

134

Test/Composition	Typical Value	Unit	Method
Density	0.944	g/cm ³	ISO 1183
Fish Eye Note	≤ 3	note	internal
FRR 21.6/5	35		
MFR 190°/21.6	6.3	g/10min	ISO1133
MFR190°/5	0.18	g/10min	ISO1133

- Test specimen from compression moulded sheet at 23°C.
- FRR values are statistical and calculated by dividing MFR values.
- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average values .