



Lacovyl® PB1172H

PVC for Plastisol

Technical datasheet

Type :

Lacovyl® PB1172H is a low molecular weight homopolymer polyvinyl chloride. It is produced by KEM ONE microsuspension polymerisation process and used to prepare plastisol pastes.


Main uses :

APPLICATION	COMPACT	FOAM
Flooring	■	■
Wallcovering	■	■
Coated Fabric	■ ■	■
UBS		
Cap sealant		
Dipping	■	
Rotational moulding	■ ■	

■ Recommended application

■ Possible application

Viscosity curves:



Viscosity measurements of plastisols with 40, 50 and 60 phr DINP by rotational rheometer after 2h at 23°C ageing.

General characteristics :

Lacovyl® PB1172H gives a **very fluid plastisol** with an **excellent filler acceptance**. Suitable for **both compact and foam applications**, it is specially recommended for low (or very low) plasticised applications or highly filled formulations. PB1172H is the choice resin for rotational moulding applications. Its good **fogging** characteristics make it suitable for automotive fabric coating.

CHARACTERISTIC	VALUE	METHOD
K-Value	67	ISO 1628-2
Viscosity number	113 ml/g	ISO 1628-2
Apparent bulk density	0,4 g/cm ³	ISO 60
Moisture content	< 0,25 %	ISO 1269
pH (Aqueous extract)	7	ISO 1060-2
Sieve retention (63 µm)	< 1 %	EN ISO 1624
Fineness (North Gauge)	120 µm	EN ISO 1524
Fogging (100°C/16hr)	< 5 mg/10 g	EN ISO 75201
Viscosity* at 5 s ⁻¹ (Equivalent Brookfield 20 rpm)	35 P or 3,5 Pa.s	EN ISO 3219
Viscosity* at 100 s ⁻¹	39 P or 3,9 Pa.s	EN ISO 3219

* viscosity measured with a mixture of PVC 100 / DINP 60 after 2 h of ageing at 23°C

Properties :

Résin

Lacovyl® PB1172H is a very fine particle size resin that can be used for very thin coatings.

Plastisol

Plastisols formulated with Lacovyl® PB1172H generally show a pseudoplastic behaviour. This allows the use of PB1172H in processes and applications that require a high degree of shear (thin coating at high speed) or in highly filled formulations where a long pot-life without a major risk of settlement is important.

Compact coating

Lacovyl® PB1172H low K-value resin improves the gelation of compact coating, particularly on the gel drum (also in highly filled formulation), and gives a gloss surface finish. With its low viscosity, PB1172H is particularly recommended in rotational moulding applications.

Cellular coating

Lacovyl® PB1172H shows a very good compromise between rheology, foam whiteness and cellular quality. It is therefore recommended for fabric coating and in wallcoverings.



■ Packaging and storage :

Lacovyl® resins are supplied in 25 kg bags, wrapped on pallets. Resin must be stored in a dry place away from all heat sources, direct or indirect. The recommended storage time for this resin is 18 months maximum. For any information on the handling and precautions required when using Lacovyl® resins, please refer to the Material Safety Data Sheet, available on our website www.kemone.com (Links).

■ Lacovyl® range for plastisol :

GRADE	K-Value	APPLICATION		VISCOSITY	SELECTION CRITERIA
		Compact	Foam		
PA1384	69	■	■	Fluid	Copolymer, gelation improvement
PB1156	66		■	Viscous	Foam whiteness
PB1172H	67	■	■	Very fluid	Low-plasticised application, moulding
PB1202	67	■	■	Very fluid	Excellent filler acceptance
PB1302 / PB1302H	70	■		Very fluid	Multi-purpose resin, gloss
PB1305H	70	■		Fluid	Adhesion on textile substrate
PB1702	78.5	■		Very fluid	Mechanical properties, semi-matness
PB1704 / PB1704H	82	■		Fluid	High mechanical properties, matness
PB1705H	82	■		Fluid	Matness, improved dark yellowing
PE1311H	70	■	■	Very viscous	Highly pseudoplastic, Very low fogging
PE1511H	75	■	■	Very viscous	Very low fogging, Embossing

■ General Information :

KEM ONE's development laboratory (LAP) is dedicated to providing an efficient technical assistance to our customers. Its specialized and modern equipment makes it a highly-skilled laboratory especially in formulation, rheology and particle size measurement.



Saint-Auban development laboratory (LAP)

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Kem One with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned. This version cancels and replaces all other version.



KEM ONE HEAD OFFICE - Immeuble Le Quadrille - 19 rue Jacqueline Auriol - 69008 LYON (FRANCE)
 N° SIREN : 538 695 040 R.C.S LYON
 N° TVA INTRACOMMUNAUTAIRE : FR45538695040
 CAPITAL SOCIAL 98 025 001 €

www.kemone.com

