

KompoGTe[®] LE1G502

Injection Molding , PP LFT +GF 50%

Application

E/E (Washer Out Tub)

Properties	Measurement condition	Test Method	Unit	Typical value
Physical				
GF Contents		ASTM D2584	wt. %	50
Color		-	-	Natural
Density		ASTM D792	-	1.31
Shrinkage		ASTM D955	%	0.10 ~ 0.30
Mechanical				
Tensile Strength at Break (3.2mm)	50 mm/min	ASTM D638	MPa	165
Flexural Strength (6.4mm)	10 mm/min	ASTM D790	MPa	195
Flexural Modulus (6.4mm)	10 mm/min	ASTM D790	MPa	11,150
Izod Impact Strength (6.4mm)		ASTM D256		
(Notched)	23 °C		J/m	245
Thermal				
Melting Point	20 °C/min	ASTM D3418	°C	163
Heat Deflection Temperature	1.8 MPa	ASTM D648	°C	163
Flammability (0.8mm)		UL94	Class	HB
※ 1Mpa = 10.197162 Kgf/cm ² , 1J/m = 0.10197 Kgf·cm/cm, (Test specimen Thickness)				
Processing Guide (Injection Molding)				

Drying Temperature(°C)	80 ~ 90	(Dehumidifying Dryer)		
Drying Time(hr)	2 ~ 4			
Processing Moisture Contents(%)	≤ 0.1			
Cylinder Temperature(°C)	Nozzle	Front	Middle	Rear
	240 ~ 260	240 ~ 260	220 ~ 240	200 ~ 220
Mold Temperature(°C)	40 ~ 80			

Updated: 2017-10-31

The values of each item in this document provide general information about the product and may be different from actual ones as reference dimensions for customer's convenience of material selection. This information cannot be viewed as a Certificate of Analysis(COA) issued by the Company to customers, nor can it be used as a basis for legal disputes such as lawsuits. The value of each item cannot be compared with the measurement result of other environment, equipment and method because it is measured under the specific condition using the existing measurement equipment and external authorized agency equipment. The characteristics described above are subject to change, and you are solely responsible for the determination and use of this product. In addition, these materials do not apply when adding pigments and other additives to the product depending on the customer's purpose of use. The value of the shrinkage factor in the above data is the value measured under the specific injection condition using our standard test piece and may be changed according to other test piece (product) and condition. Therefore, it is the customer's responsibility to apply the correction by considering the required characteristics of the molded product, the mold design condition, the product shape, the injection conditions, etc. Even if there is a difference in the shrinkage rate of the product in the mold manufactured by applying this shrinkage ratio, we also assume no guarantee or liability.

Contact Uswww.kolonplastics.com

Domestic Sales

TEL : +82-2-3677-3621 / FAX :+82-2-3677-3556

Domestic Sales(Yeongnam)

TEL : +82-53-253-3792 / FAX : +82-53-253-3793

Global Sales

TEL : +82-2-3677-3623 / FAX : 02-3677-3558

R&D Division

TEL : +82-54-421-1490 / FAX : +82-54-421-1449

Updated: 2017-10-31

The values of each item in this document provide general information about the product and may be different from actual ones as reference dimensions for customer's convenience of material selection. This information cannot be viewed as a Certificate of Analysis(COA) issued by the Company to customers, nor can it be used as a basis for legal disputes such as lawsuits. The value of each item cannot be compared with the measurement result of other environment, equipment and method because it is measured under the specific condition using the existing measurement equipment and external authorized agency equipment. The characteristics described above are subject to change, and you are solely responsible for the determination and use of this product.

In addition, these materials do not apply when adding pigments and other additives to the product depending on the customer's purpose of use. The value of the shrinkage factor in the above data is the value measured under the specific injection condition using our standard test piece and may be changed according to other test piece (product) and condition. Therefore, it is the customer's responsibility to apply the correction by considering the required characteristics of the molded product, the mold design condition, the product shape, the injection conditions, etc. Even if there is a difference in the shrinkage rate of the product in the mold manufactured by applying this shrinkage ratio, we also assume no guarantee or liability.