



SPESIN[®] KP270EX

PBT, High viscosity, Extrusion grade

Application

OFC loose tube, Auto(Cable)

Properties	Measurement condition	Test Method	Unit	Typical value
Physical				
Density		ASTM D792	–	1.31
Water Absorption	23 °C, H ₂ O, 24hr	ASTM D570	%	0.08
Melt Index	250 °C, 2160g	ASTM D1238	g/10min	10 ± 2
Viscosity number	Phenol : 1,2 Dichlorobenzene = 1 : 1	ISO 1628-5	mL/g	160
Mechanical				
Tensile Strength at Break	(3.2mm) 50 mm/min	ASTM D638	MPa	51
Elongation at Break	(3.2mm) 50 mm/min	ASTM D638	%	> 100
Flexural Strength	(3.2mm) 5 mm/min	ASTM D790	MPa	90
Flexural Modulus	(3.2mm) 5 mm/min	ASTM D790	MPa	2,550
Izod Impact Strength	(6.4mm)	ASTM D256		
(Notched)	23 °C		J/m	59
Thermal				
Melting Point	20 °C/min	ASTM D1525	°C	224
Heat Deflection Temperature	0.45 MPa	ASTM D648	°C	60
	1.82 MPa	ASTM D648	°C	170
Flammability	(0.8mm)	UL94	Class	HB

Updated: 2019-10-25

The values of each item in this document provide general information about the product and may be different from actual ones as reference dimensions for customer's convenience of material selection. This information cannot be viewed as a Certificate of Analysis(COA) issued by the Company to customers, nor can it be used as a basis for legal disputes such as lawsuits. The value of each item cannot be compared with the measurement result of other environment, equipment and method because it is measured under the specific condition using the existing measurement equipment and external authorized agency equipment. The characteristics described above are subject to change, and you are solely responsible for the determination and use of this product. In addition, these materials do not apply when adding pigments and other additives to the product depending on the customer's purpose of use. The value of the shrinkage factor in the above data is the value measured under the specific injection condition using our standard test piece and may be changed according to other test piece (product) and condition. Therefore, it is the customer's responsibility to apply the correction by considering the required characteristics of the molded product, the mold design condition, the product shape, the injection conditions, etc. Even if there is a difference in the shrinkage rate of the product in the mold manufactured by applying this shrinkage ratio, we also assume no guarantee or liability.

Processing Guide (Extruding)

Drying Temperature(℃)	100~120	(Dehumidifying Dryer)		
Drying Time(hr)	3~5			
Processing Moisture Contents(%)	≤ 0.04			
Cylinder Temperature(℃)	Nozzle	Front	Middle	Rear
	260~275	260~270	260~270	250~265
Cooling Temperature(℃)	1st zone	2nd zone	3rd zone	
	50~60	50~60	20~30	
Extruder	L/D=24			
Compression Ratio	3:1			

Contact Us
www.kolonplastics.com
Domestic Sales

TEL : +82-2-3677-3621 / FAX : +82-2-3677-3556

Domestic Sales(Yeongnam)

TEL : +82-53-253-3792 / FAX : +82-53-253-3793

Global Sales

TEL : +82-2-3677-3623 / FAX : 02-3677-3558

R&D Division

TEL : +82-54-421-1490 / FAX : +82-54-421-1449

Updated: 2019-10-25

The values of each item in this document provide general information about the product and may be different from actual ones as reference dimensions for customer's convenience of material selection. This information cannot be viewed as a Certificate of Analysis(COA) issued by the Company to customers, nor can it be used as a basis for legal disputes such as lawsuits. The value of each item cannot be compared with the measurement result of other environment, equipment and method because it is measured under the specific condition using the existing measurement equipment and external authorized agency equipment. The characteristics described above are subject to change, and you are solely responsible for the determination and use of this product. In addition, these materials do not apply when adding pigments and other additives to the product depending on the customer's purpose of use. The value of the shrinkage factor in the above data is the value measured under the specific injection condition using our standard test piece and may be changed according to other test piece (product) and condition. Therefore, it is the customer's responsibility to apply the correction by considering the required characteristics of the molded product, the mold design condition, the product shape, the injection conditions, etc. Even if there is a difference in the shrinkage rate of the product in the mold manufactured by applying this shrinkage ratio, we also assume no guarantee or liability.