

KEP 2380

*beyond
the best*

Ethylene Propylene Diene Terpolymer

KUMHO POLYCHEM

Product Data Sheet

Product Description	Features
KEP2380 is an EPDM rubber with Bimodal molecular weight distribution, low ethylene contents. It can be used to 60 ~ 70 Shore A dense body sealing, Radiator hose, molded goods, gaskets.	- High loadability - Superior processability - Good cure performance - Fast curing for continuous vulcanization - Improves productivity & collapse resistance

Test items	Sale Specifications	Unit	Test Method
Volatile Matter	Max 0.75	wt %	ASTM D5668
Mooney Viscosity ML(1+8)@125 °C	82.0 ± 5.0	MU	ASTM D1646
Ethylene Contents	55.5 ± 2.0	wt %	ASTM D3900
ENB Contents	5.7 ± 0.5	wt %	ASTM D6047

Other Products Features

Product Form	Bale
Packaging	25 kg/Bale in Carton/Mesh Box, LDPE film, 750 kg(25 kg × 30),
Shelf Life	24 months from date of production at room temperature in dry condition, exposure to light has to be avoided
The Others	RoHS Free

Contact Information

Head Office	8F, East Wing, Signature Tower, #100 Cheonggyecheon-ro, Jung-gu, Seoul, Korea 82-2-6961-0000
Plant	613 Sandanjungang-ro, Yeosu, Jeonnam, Korea 82-61-688-2822
Revision Date	12/02/2020
Revision No.	12