

WeConnectScience



# SG175H

## Description

SG175H is an ABS product for injection molding, designed to have a super gloss level and good UV resistance.

## Key Features

UV Resistance, Super Gloss

## Application

Refrigerator, Washing Machine, Electrical/Electronic Products

| Properties                  | Condition                            | Method     | Unit     | SG175H    |
|-----------------------------|--------------------------------------|------------|----------|-----------|
| <b>Physical</b>             |                                      |            |          |           |
| Specific Gravity            | 23°C                                 | ASTM D792  |          | 1.05      |
| Mold Shrinkage              | 23°C, 3.2mm                          | ASTM D955  | %        | 0.4 ~ 0.7 |
| Melt Flow Index             | 220°C, 10kg                          | ASTM D1238 | g/10min  | 32        |
| <b>Mechanical</b>           |                                      |            |          |           |
| Tensile Strength at Yield   | 23°C, 50mm/min, 3.2mm                | ASTM D638  | MPa      | 43        |
| Tensile Elongation at Break | 23°C, 50mm/min, 3.2mm                | ASTM D638  | %, (Min) | 10        |
| Flexural Strength           | 23°C, 10mm/min, 6.4mm                | ASTM D790  | MPa      | 72        |
| Flexural Modulus            | 23°C, 10mm/min, 6.4mm                | ASTM D790  | MPa      | 2350      |
| Izod Impact Strength        | Notched, 3.2mm, 23°C                 | ASTM D256  | J/m      | 215       |
| Izod Impact Strength        | Notched, 6.4mm, 23°C                 | ASTM D256  | J/m      | 190       |
| Rockwell Hardness           | R-Scale                              | ASTM D785  |          | 108       |
| <b>Thermal</b>              |                                      |            |          |           |
| Heat Deflection Temperature | Edgewise, 1.82MPa, 6.4mm, Unannealed | ASTM D648  | °C       | 87        |
| Vicat Softening Temperature | 50N, 50°C/h                          | ASTM D1525 | °C       | 95        |

## Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date: 2021-05-07 Issued Date : 2023-03-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

WeConnectScience



# SG175H

## Description

SG175H is an ABS product for injection molding, designed to have a super gloss level and good UV resistance.

## Key Features

UV Resistance, Super Gloss

## Application

Refrigerator, Washing Machine, Electrical/Electronic Products

## Processing Guide (Injection Molding)

| Processing Parameters | Unit | Value     |
|-----------------------|------|-----------|
| Drying Temperature    | °C   | 70 ~ 80   |
| Drying Time           | hrs  | 3 ~ 4     |
| Injection Temperature | °C   | 200 ~ 250 |
| Mold Temperature      | °C   | 40 ~ 80   |
| Screw Speed           | rpm  | 30 ~ 60   |

## Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated Date: 2021-05-07 Issued Date : 2023-03-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.