

WeConnectScience



TR556

Description

TR556 is a Transparent ABS product for injection molding and extrusion, designed to have transparency, good chemical resistance, and high impact strength.

Key Features

Transparency, Chemical Resistance, High Impact Strength

Application

Electrical/Electronic Products, Extrusion Profile/Sheet, other Miscellaneous Goods

Properties	Condition	Method	Unit	TR556
Physical				
Specific Gravity	23°C	ASTM D792		1.09
Mold Shrinkage	23°C, 3.2mm	ASTM D955	%	0.4 ~ 0.7
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	5
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	49
Tensile Elongation at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	5
Tensile Elongation at Break	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	15
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	79
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2300
Izod Impact Strength	Notched, 3.2mm, 23°C	ASTM D256	J/m	195
Izod Impact Strength	Notched, 3.2mm, -30°C	ASTM D256	J/m	80
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	195
Izod Impact Strength	Notched, 6.4mm, -30°C	ASTM D256	J/m	80
Rockwell Hardness	R-Scale	ASTM D785		109
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	85
Heat Deflection Temperature	Edgewise, 0.46MPa, 6.4mm, Unannealed	ASTM D648	°C	93
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Annealed	ASTM D648	°C	91
Heat Deflection Temperature	Edgewise, 0.46MPa, 6.4mm, Annealed	ASTM D648	°C	96
Vicat Softening Temperature	50N, 50°C/h	ASTM D1525	°C	93
Optical				
Haze		ASTM D1003	%	2.3
Luminous Transmittance	3.2mm	ASTM D1003	%	90

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date: 2021-05-07 Issued Date : 2023-03-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

WeConnectScience



TR556

Description

TR556 is a Transparent ABS product for injection molding and extrusion, designed to have transparency, good chemical resistance, and high impact strength.

Key Features

Transparency, Chemical Resistance, High Impact Strength

Application

Electrical/Electronic Products, Extrusion Profile/Sheet, other Miscellaneous Goods

Updated Date: 2021-05-07 Issued Date : 2023-03-09

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.