



LG EVA EC28007

Ethylene Vinyl Acetate Copolymer

Applications

- Wire and Cable Compound

Performance

- Uniform VA Contents and MI
- Excellent surface finish
- High filler loading (Carbon black, Flame retardant agent)
- Contaminants free
- Excellent electrical & mechanical property

Typical properties

Characteristics	Test Method	Unit	Value
Physical⁽¹⁾			
VA Contents	LG	%	28
Density	ASTM D1505	g/cm ³	0.951
MFR (190 °C, 2.16Kg)	D1238	g/10min	6.5
Mechanical⁽²⁾			
Tensile Strength at Break	D638 ⁽³⁾	Mpa	12.0
Elongation at Break	D638 ⁽³⁾	%	800
Hardness			
Shore hardness (Shore A)	D2240	-	78
Thermal			
Melting Temperature	LG	°C	76

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 500 mm/min.

Processing information

- **EC28007** may be processed on conventional equipment.

For additional sales, order and technical assistance

Revised : 12/05/2016

Head office PO Division, LG Chem Ltd.
Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouido-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932,6613

PO. TS team **PO.Tech Center**
188, Munji-ro, Yuseong-gu., Daejeon, 34122, Korea
Tel. 82-42-722-5055

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."



LG EVA EC28007

Ethylene Vinyl Acetate Copolymer

Storage and handling Recommendations

Ethylene Vinyl Acetate Copolymers are available in free-flowing pelletized form designed for use in conventional polymer fabrication systems.

Ethylene Vinyl Acetate Copolymer storage and handling of these product is extremely important for the products to remain flowable for transport and processing without pellet blocking.

- **To prevent pellet blocking**
 - To minimize static load, do not double stack pallets.
 - Keeping storage and handling temperature between 10 ~ 25 °C.
 - Store the resins in the warehouse to protect from exposure to elevated temperature which is not to exceed 35 °C.
 - Consume the resins on a first in, first out basis.

For additional sales, order and technical assistance

Revised : 12/05/2016

Head office PO Division, LG Chem Ltd.
Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouido-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932,6613

PO. TS team PO.Tech Center
188, Munji-ro, Yuseong-gu., Daejeon, 34122, Korea
Tel. 82-42-722-5055

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."