

Solution*Partner*

Technical Data Sheet

Luprene® LG501



SolutionPartner

LG501

Styrene-Butadiene-Styrene

Description

Linear Structure, Non-oil Extended Grade
Thermoplastic Elastomer

Application

Asphalt Modifier, Plastic Modifier
Compounding, Adhesives, etc

Physical Properties

Test Item	Test method	Unit	Typical Value
Structure	-	-	Linear
Styrene Content	LSY-QB-SD015 ¹⁾	%	31.0
Density	ISO 2781	g/cm ³	0.94
T.S.V ²⁾	ASTM D445	cSt	13.2
Hardness	ASTM D2240	Shore A	79
Volatile Matter	ASTM D1416	%	< 0.6
Yellow Index	ASTM D1925	-	< 6
Other			
Physical Form	Porous pellet(LG501S), Powder(LG501W)		
Packaging	Paper bag(20kg), Flecon bag(500kg)		

1) LG Chem Test Method

2) T.S.V.: Toluene Solution Viscosity 5%

The information contained herein is intended for the named recipients only. It may contain privileged and confidential information or otherwise protected under applicable laws. If you have received this document in error, please immediately notify the sender and shred the documents and any attachments without any copying or disclosure of the contents. LG Chem, Ltd.