

SolutionPartner


LUMIPLAS LD8890H

Injection & Extrusion molding grade

Description

Light diffusion
Weatherability

Application

(LED) Lamp cover, Signboard
Lighting decoration of electronic device

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ASTM D792	-	1.20
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	0.5-0.8
Melt Flow Rate	300°C/1.2kg	ASTM D1238	g/10min	11
Outdoor Suitability		UL746C		f1
Mechanical				
Tensile Strength, 3.2mm @ Yield	50mm/min	ASTM D638	kg/cm ²	630
Tensile Elongation, 3.2mm @ Break	50mm/min	ASTM D638	%	>100
Flexural Strength, 6.4mm	15mm/min	ASTM D790	kg/cm ²	950
Flexural Modulus, 6.4mm	15mm/min	ASTM D790	kg/cm ²	23,000
IZOD Impact Strength, 3.2mm (Notched)	23°C	ASTM D256	kg·cm/cm	80
	-30°C		kg·cm/cm	
Rockwell Hardness	R-Scale	ASTM D785	-	118
Thermal				
Heat Deflection Temperature, 6.4mm (Unannealed)	18.6kg	ASTM D648	°C	130
	4.6kg		°C	
Flammability		UL94		
0.5mm			class	V-2
1.6mm			class	V-2
2.5mm			class	V-2
3.0mm			class	V-2
Relative Temperature Index		UL 746B		
Electrical			°C	120
Mechanical with Impact			°C	105
Mechanical without Impact			°C	120
Optical				
Transparency (@1mm)		JIS K7361	%	89

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Updated : 10-Dec-15

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

SolutionPartner


LUMIPLAS LD8890H

Injection & Extrusion molding grade

Description

Light diffusion
Weatherability

Application

(LED) Lamp cover, Signboard
Lighting decoration of electronic device

Processing Guide (Injection Molding)

Processing Parameters		Unit	Value
Drying Temperature		°C	100 ~ 120
Drying Time		hrs	3 ~ 5
Maximum Moisture Content		%	0.02
Melt Temperature		°C	300 ~ 320
Cylinder Temperature	Rear	°C	260 ~ 280
	Middle	°C	280 ~ 300
	Front	°C	290 ~ 310
Nozzle Temperature		°C	290 ~ 310
Mold Temperature		°C	80 ~ 120
Back Pressure		kg/cm ²	10 ~ 40
Screw Speed		rpm	40 ~ 70

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Processing Guide (Extrusion Molding)

Processing Parameters		Unit	Value
Drying Temperature		°C	100 ~ 120
Drying Time		hrs	3 ~ 4
Maximum Moisture Content		%	0.02
Melt Temperature		°C	300 ~ 320
Barrel Temperature	Zone 1	°C	260 ~ 280
	Zone 2	°C	270 ~ 300
	Zone 3	°C	270 ~ 300
	Zone 4	°C	270 ~ 300
Adapter Temperature		°C	280 ~ 300
Die Temperature		°C	260 ~ 295
Roll Stack Temperature	Top	°C	120 ~ 150
	Middle	°C	120 ~ 150
	Bottom	°C	120 ~ 150

Note) Recommend initial lower temperatures settings to avoid material degradation/hang-up in die & purge material from extruder prior to shutdown.

Updated : 10-Dec-15

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.