

LUTENE[®] LB7500

Low Density Polyethylene

Applications

- Flexible package(tie layer or sealant layer of laminating film), Paper and paper board

Description

- LUTENE[®] LB7500 is mainly intended for extrusion coating and can be processed at high speed with uniform thickness and width.
- LUTENE[®] LB7500 has a good adhesion strength with Al-foil, polymer film, paper, paper board and other substrate and excellent neck-in characteristics.
- LUTENE[®] LB7500 contains no additives.
- LUTENE[®] LB7500 complies with U.S. FDA 21CFR 177.1520 C and Japanese Ministry of Health and Welfare Notification N.20 Standard.

Typical properties

Characteristics	Test Method	Unit	Value
Physical⁽¹⁾			
MFR(190 °C, 2.16Kg)	ASTM D1238	g/10min	7.2
Density	D792	g/cm ³	0.918
Mechanical⁽²⁾			
Tensile Strength at Yield	D638	Mpa	8.8
Tensile Strength at Break	D638	Mpa	11.3
Elongation at Break	D638	%	>500
Shore hardness(Shore D)	D2240	-	43
Thermal			
Melting Temperature	LG Method	°C	106
Vicat Softening Point	D1525	°C	83
Thermal			
Neck-in (at speed 150m/min)	LG Method	mm	25
Max. Coating Speed (at weight 9g/m ²)	LG Method	m/min	500
Min. Coating Weight (at speed 500m/min)	LG Method	g/m ²	9

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

For additional sales, order and technical assistance

Head office PO Division, LG Chem Ltd.
Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouido-daero 128, Yeongdeungpo-gu Seoul, Korea.

TS&D **TECH Center. Polyolefin**
188, Munji-ro, Yuseong-gu, Daejeon, 34122, Korea.
Tel. 82-42-722-5074

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.



LUTENE[®] LB7500

Low Density Polyethylene

Processing information

- LUTENE[®] LB7500 can be easily processed on all standard extrusion coating equipment.
- Optimum melt temperature on commercial extrusion coating equipment is range of 280 to 330 °C.

Storage and handling Recommendations

- LUTENE[®] LB7500 should be stored in a dry and dust free conditions.
- Keep below 45 °C taking away from direct sunlight

For additional sales, order and technical assistance

Head office PO Division, LG Chem Ltd.

Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouidaero 128, Yeongdeungpo-gu Seoul, Korea.

TS&D**TECH Center. Polyolefin**

188, Munji-ro, Yuseong-gu, Daejeon, 34122, Korea.
Tel. 82-42-722-5074

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products."