



LUTENE[®] XL2802BK

Semi-conductive

Applications

- Excellent-smoothness extra clean semi-conductive compound for conductor and bonded insulation shielding of high voltage power cable

Description

- LUTENE[®] XL2802BK is a cross-linkable semi-conductive shielding compound for conductor and bonded insulation shielding of high voltage power cables.
- LUTENE[®] XL2802BK is compatible with both copper and aluminum conductors. LUTENE[®] XL2802BK was specifically developed to provide a excellent-smoothness surface yielding a more perfect interface between extruded shield and the insulation. As a result, significantly improved cable performance can be expected.
- LUTENE[®] XL2802BK has stable volume resistivity characteristics at elevated temperature.

Characteristics

- ① Excellent Surface Smoothness
- ② Excellent Electrical Properties
- ③ Excellent Physical and Thermal Properties
- ④ Long-run Extrusion without Scorch

Specification

- LUTENE[®] XL2802BK meets the property requirement of the following material specifications.
 - ① AEIC CS8
 - ② AEIC CS 7-93
 - ③ IEC 60502 / IEC 60840
 - ④ ICEA S-94-649, S-66-524 / NEMA WC74

Package

- Standard package : 500kg Carton Box
- Other package to customer's needs are also available.

For additional sales, order and technical assistance

Revised : 12/05/2016

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932,6613

PO. TS team PO.Tech Center
188, Munji-ro, Yuseong-gu,, Daejeon, 34122, Korea
Tel. 82-42-722-5055

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.



LUTENE[®] XL2802BK

Semi-conductive

Processing information

- LUTENE[®] XL2802BK provides excellent surface finish and outstanding output rates, when processing conditions are optimized for the actual processing equipment and cable dimension.
- For optimum results, use melt extrusion temperatures in the suggested range of 90 to 115 °C.
- Dehumidified hopper drying at 40~60 °C for 4 hours before extrusion is recommended to remove moisture.

Typical properties

Characteristics	Test Method	Test Condition	Unit	Value
Physical				
Density, Base Resin	ASTM D1505	23 °C	g/cm ³	1.12
Tensile Strength	ASTM D638	200mm/min	Mpa	> 14.7
Elongation at Break	ASTM D638	200mm/min	%	> 160
Tensile Strength Retention after	ASTM D638	135 °C, 168hr	%	> 90
Elongation Retention after	ASTM D638	135 °C, 168hr	%	> 90
Low Temperature Brittleness	ASTM D746	-	°C	- 40 °C No crack
Moisture Content	Karl Fischer	-	ppm	< 500
Electrical				
DC Volume Resistivity	ASTM D991	23 °C	Ω·cm	< 100
	ASTM D991	90 °C	Ω·cm	< 300
	ASTM D991	135 °C	Ω·cm	< 500

* Measured on compression molded specimen. Cure times were 15min at 180 °C

** NOTE : Values given above should only be used as a guide and should not be considered as a firm specification or guarantee.

For additional sales, order and technical assistance

Revised : 12/05/2016

Head office PO Division, LG Chem Ltd.

Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouido-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932, 6613

PO. TS team PO.Tech Center

188, Munji-ro, Yuseong-gu,, Daejeon, 34122, Korea
Tel. 82-42-722-5055

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.