



LUTENE[®] XL2808BK

Semi-conductive

Applications

- Cross-linkable semi-conductive compound for conductor and bonded insulation shielding of medium voltage power cables with rated voltage up to 35kV

Description

- LUTENE[®] XL2808BK has an excellent electrical properties and assists in obtaining a minimum shrinkback on aluminum conductor, especially solid conductor.
- LUTENE[®] XL2808BK is specifically developed to provide a smooth surface yielding a more perfect interface between the extruded shield and the insulation.
- LUTENE[®] XL2808BK has stable volume resistivity characteristics at elevated temperatures and is formulated with a polymer system that has demonstrated compatibility with copper conductor.

Characteristics

- ① Excellent Electrical Property
- ② Excellent Physical and Thermal Property
- ③ Excellent Surface Smoothness

Specification

- LUTENE[®] XL2808BK meets the property requirement of the following material specifications.
 - ① AEIC CS8
 - ② ICEA S-94-649
 - ③ IEC 60502
 - ④ BS 6622

Package

- Standard package : 600kg Carton Box
- Other package to customer's needs are also available.

For additional sales, order and technical assistance

Revised : 12/05/2016

Head office PO Division, LG Chem Ltd.
Yeoui-do P.O.Box 672, 21st floor LG Twin Tower,
Yeoui-daero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932,6613

PO. TS team **PO.Tech Center**
188, Munji-ro, Yuseong-gu., Daejeon, 34122, Korea
Tel. 82-42-722-5055

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.



LUTENE[®] XL2808BK

Semi-conductive

Processing information

- LUTENE[®] XL2808BK provides excellent surface finish and outstanding output rates over a broad range of extrusion conditions. For optimum results, use melt extrusion temperatures in the suggested range of 90 to 115 °C. Specific machine settings will depend on the extruder design and must be established through conventional practices.
- Hopper drying at 40~60 °C for 4 hours before extrusion is recommended to remove moisture.

Typical properties

Characteristics	Test Method	Test Condition	Unit	Value
Physical				
Density, Base Resin	ASTM D1505	23 °C	g/cm ³	1.14
Tensile Strength	ASTM D638	200mm/min	Mpa	> 12.5
Elongation at Break	ASTM D638	200mm/min	%	> 200
Tensile Strength Retention after	ASTM D638	135 °C, 168hrs	%	> 85
Elongation Retention after	ASTM D638	135 °C, 168hrs	%	> 85
Low Temperature Brittleness	ASTM D746	-	°C	-25 °C no crack
Moisture Content	Karl Fischer	-	ppm	< 1,000
Electrical				
DC Volume Resistivity	ASTM D991	23 °C	Ω·cm	<100
	ASTM D991	90 °C	Ω·cm	<1,000

* Measured on compression molded specimen. Cure times were 15min at 180 °C

** NOTE : Values given above should only be used as a guide and should not be considered as a firm specification or guarantee.

For additional sales, order and technical assistance

Revised : 12/05/2016

Head office PO Division, LG Chem Ltd.

Yeouido P.O.Box 672, 21st floor LG Twin Tower,
Yeouidaero 128, Yeongdeungpo-gu Seoul, Korea.
Tel. 82-2-3773-3932,6613

PO. TS team PO.Tech Center

188, Munji-ro, Yuseong-gu., Daejeon, 34122, Korea
Tel. 82-42-722-5055

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.