

DATASHEET

ASTM Property



Grade	UL314P
Product	LLDPE

General Information

Key Features	- Good mechanical properties, Excellent optical properties, - Good processability, Gel free - Including anti-blocking agent
--------------	---

Applications	Protection film, Lamination film
--------------	----------------------------------

Item	Measuring Method	Unit	Value
------	------------------	------	-------

Physical

Melt Flow Index	ASTM D1238	g/10min	1.1
-----------------	------------	---------	-----

Density	ASTM D1505	g/cm ³	0.920
---------	------------	-------------------	-------

Blown Film Properties (40 μm)

Ultimate Tensile Strength	MD	ASTM D882	kgf/cm ²	430
	TD			390

Ultimate Elongation	MD	ASTM D882	%	740
	TD			760

Elmendorf Tear Strength	MD	ASTM D1922	g/μm	6
	TD			11

Dart Impact Strength	ASTM D1709	g	170
----------------------	------------	---	-----

Haze	ASTM D1003	%	11
------	------------	---	----

Gross (45°)	ASTM D2457	%	74
-------------	------------	---	----

· Processing Condition : Φ50mm LLDPE Blown Film Extruder
Temperature 180°C, Die Gap 2.2mm, BUR 2.1, FLH 32cm

1. Physical Properties : these are not to be construed as specifications
2. ISO 9001, 14001, /TS 16949

* The last update date : 2021/10/01