



2013

POPELEN HSP-375
PP BLOCK COPOLYMER
General Information
Characteristics

Low Density, Anti Scratch

Applications

Automotive Parts (Door Trim)

Physical Properties¹

Physical	Test Method	Unit	Nominal Values
Melt Flow Index (230 °C)	ASTM D1238	g/10min	22.0
Density	ASTM D792	g/cm ³	0.97
Mechanical			
Yield Strength	ASTM D638	kgf/cm ²	250
Elongation	ASTM D638	%	80
Flexural Modulus	ASTM D790	kgf/cm ²	20,000
Flexural Strength	ASTM D790	kgf/cm ²	380
IZOD Impact Strength (23 °C)	ASTM D256	kgf·cm/cm	15.0
IZOD Impact Strength (-10 °C)	ASTM D256	kgf·cm/cm	6.0
Rockwell Hardness	ASTM D785	R	75
Thermal			
Heat Distortion Temp. (4.6kgf/cm ²)	ASTM D648	°C	125

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com