

LOTTE CHEMICAL

2013

POPELEN RX-20000

PP BLOCK COPOLYMER

General Information

● Characteristics

High Stiffness, High Impact Strength

● Applications

Bumper Fascia

Physical Properties¹

Physical	Test Method	Unit	Nominal Values
Melt Flow Index (230 °C)	ASTM D1238	g/10min	28.0
Density	ASTM D792	g/cm ³	0.97
Mechanical			
Yield Strength	ASTM D638	kgf/cm ²	200
Elongation	ASTM D638	%	200
Flexural Modulus	ASTM D790	kgf/cm ²	18,000
Flexural Strength	ASTM D790	kgf/cm ²	-
IZOD Impact Strength (23 °C)	ASTM D256	kgf·cm/cm	50.0
IZOD Impact Strength (-30 °C)	ASTM D256	kgf·cm/cm	7.0
Rockwell Hardness	ASTM D785	R	-
Thermal			
Heat Distortion Temp. (4.6kgf/cm ²)	ASTM D648	°C	115

NOTE

ISO 9001, 14001, /TS 16949

¹ Physical Properties : these are not to be construed as specifications

www.lottechem.com